
**Steel wire ropes — Determination of the
actual modulus of elasticity**

Câbles en acier — Détermination du module effectif d'élasticité



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 12076:2002

© ISO 2002

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 12076 was prepared by Technical Committee ISO/TC 105, *Steel wire ropes*.

Introduction

This International Standard is intended to provide manufacturers, suppliers and independent testing bodies with a uniform testing method for determining the modulus of steel wire rope.

Modulus values depend on the condition of the rope, and it is thus necessary to know the actual condition under which the modulus is to be, or has been, determined. The three usual conditions are

- initial (as manufactured),
- partially-bedded, or
- final bedded.

It is important, too, to recognize that steel wire ropes do not possess a normal modulus of elasticity, but an “apparent” one, which can be determined between fixed loads. This is referred to as the *rope modulus*.

STANDARDSISO.COM : Click to view the full PDF of ISO 12076:2002

Steel wire ropes — Determination of the actual modulus of elasticity

1 Scope

This International Standard specifies a method for determining, by test and calculation, the actual modulus of steel wire ropes within a specified load range.

2 Normative reference

The following normative document contains provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent edition of the normative document indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 7500-1, *Metallic materials — Verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Verification and calibration of the force-measuring system*

3 Terms and definitions

For the purposes of this International Standard, the following terms and definitions apply.

3.1 initial rope modulus

E_i
constant in the relationship between stress and strain when measured during the first (initial) loading of the rope following manufacture

3.2 partially-bedded rope modulus

E_{p-b}
constant in the relationship between stress and strain when measured with the rope in a partially-bedded condition

3.3 final rope modulus

E_f
constant in the relationship between stress and strain when measured with the rope in its bedded condition

3.4 bedded condition

condition at which repeated extension readings are consistent at both ends of the force range

4 Test piece

The test piece shall be representative of the rope as a whole and be free from defects.

Its length shall be such that the free length between grips or end termination is at least equivalent to $30 \times$ nominal rope diameter.

5 Gauge length

The gauge length of the extensometer, when employed, shall be at least equivalent to $15 \times$ nominal rope diameter for ropes up to 60 mm in diameter. For rope sizes of more than 60 mm diameter, the gauge length shall be a minimum of one lay length or a minimum of 900 mm, whichever is the greater.

6 Tensile testing machine

The tensile testing machine shall be in accordance with ISO 7500-1.

7 Test method

When an extensometer is used to measure extension, apply a force equivalent to 10 % of the minimum breaking force or nominal breaking strength of the rope, attach and zero the extensometer, then measure the gauge length (l_i).

When the modulus is to be determined with the rope in its initial condition, increase the force to a value of no greater than 30 % of the minimum breaking force, or nominal breaking strength, of the rope. Note the extensometer readings (x_1 and x_2) at forces equivalent to 10 % and 30 % ($F_{10\%}$ and $F_{30\%}$), respectively, of the minimum breaking force of the rope.

When the modulus is to be determined with the rope in a partially-bedded or fully-bedded condition increase the force to a value no greater than 50 % of the minimum breaking force of the rope.

Decrease the force to a value equivalent to 5 % of the minimum breaking force of the rope.

Continue applying and reducing the force in a cyclical manner until the test piece is bedded, either partially or fully, as required.

If cycling is stopped before the rope reaches its bedded condition, i.e. the rope is only partially-bedded, the number of cycles shall be recorded [see 9, h)].

If other minimum and maximum values of force are used, the difference between them should be not greater than 20 % of the minimum breaking force of the rope.

NOTE During loading and unloading of the rope a hysteresis effect will be observed. To avoid confusion, the readings of extensions for the purpose of the calculation are taken when the load is increasing.

Then, unless other values (e.g. for lift ropes) of force are agreed between the purchaser and the manufacturer, apply a force equivalent to 10 % of the minimum breaking force, and note the force ($F_{10\%}$) and the extensometer reading (x_1). Increase the force until it is equivalent to 30 % of the minimum breaking force, and note the force ($F_{30\%}$) and the extensometer reading (x_2).