

---

---

**Thermal spraying — Determination of the  
deposition efficiency for thermal spraying**

*Projection thermique — Détermination du rendement de dépôt en  
projection thermique*

STANDARDSISO.COM : Click to view the full PDF of ISO 17836:2004



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 17836:2004

© ISO 2004

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 17836 was prepared by the European Committee for Standardization (CEN) in collaboration with Technical Committee ISO/TC 107, *Metallic and other inorganic coatings*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

Throughout the text of this document, read “...this European Standard...” to mean “...this International Standard...”.

Annex ZA provides a list of corresponding International and European Standards for which equivalents are not given in the text.

## Contents

	page
Foreword.....	v
Introduction.....	vi
1 Scope .....	1
2 Normative references .....	1
3 Terms and definitions .....	1
4 Test pieces, equipment, working and auxiliary materials .....	1
5 Test implementation .....	2
6 Determination of deposition efficiency .....	3
7 Test report .....	3
8 Designation .....	4
Annex A (normative) Test piece – Pipe (A) .....	5
Annex B (normative) Test piece – Plate (B) .....	6
Annex C (informative) Record for the determination of the deposition efficiency rate – Example .....	7
Annex ZA (normative) Normative references to international publications with their relevant European publications .....	8

STANDARDSISO.COM : Click to view the full PDF of ISO 17836:2004

## Foreword

This document (EN ISO 17836:2004) has been prepared by Technical Committee CEN/TC 240 “Thermal spraying and thermally sprayed coatings”, the secretariat of which is held by DIN, in collaboration with Technical Committee ISO/TC 107 “Metallic and other inorganic coatings”.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2005, and conflicting national standards shall be withdrawn at the latest by May 2005.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard : Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

STANDARDSISO.COM : Click to view the full PDF of ISO 17836:2004

## Introduction

This document includes the definitions for determining the deposition efficiency for thermal spraying. The document describes the test implementation procedure to determine the deposition efficiency for an individual spray process and a spray material when using a defined test piece.

The deposition efficiency calculated on a test piece according to this document needs not to correspond to the deposition efficiency on a component.

STANDARDSISO.COM : Click to view the full PDF of ISO 17836:2004

## 1 Scope

It is essential to apply this document if data concerning the deposition efficiency of a spray process in connection with a defined spray material are required.

This document defines the procedure for determining the deposition efficiency for a thermal spray process in connection with a spray material and related equipment and auxiliary materials. It is applicable for all thermal spray processes (see EN 657) and all wire, rod, cord and powder spray materials.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 657, *Thermal spraying — Terminology, classification.*

EN 1274, *Thermal spraying — Powders — Composition — Technical supply conditions.*

EN 13507, *Thermal spraying — Pre-treatment of surfaces of metallic parts and components for thermal spraying.*

EN ISO 14919, *Thermal spraying — Wires, rods and cords for flame and arc spraying — Classification — Technical supply conditions (ISO 14919:2001).*

## 3 Terms and definitions

For the purposes of this document, the following term and definition applies.

### 3.1

#### **deposition efficiency (DE)**

ratio of the mass of the spray material deposited on the test piece under standard conditions to the mass of the spray material required and fed through for this purpose in %

## 4 Test pieces, equipment, working and auxiliary materials

a) Test pieces can be selected from:

- 1) a test pipe, dimensions according to Annex A;
- 2) a test plate, dimensions according to Annex B.

b) Equipment/working materials:

- 1) spray equipment;
- 2) handling system (if spray process is mechanised);
- 3) metering device (feeder for wire, rod, cord or powder);
- 4) fuel gases/fuel/electric energy;
- 5) plasma gases;
- 6) spray cabin;
- 7) filter/exhaust system.


c) Auxiliary materials:

- 1) clamping device for test piece;
- 2) scales (minimum accuracy 1 g).

## 5 Test implementation

- The test pieces shall be prepared according to specifications, e.g. degreased and grit-blasted (see also EN 13507). This procedure shall be documented.
- The mass of the prepared test piece shall be determined and documented.
- The feed rate of the spray material shall be determined in g/min in at least two run-throughs in order to calculate the mean value.
- The test pieces shall be coated applying the spray parameters selected. If risk of overheating exists, suitable cooling steps shall be taken. All parameters shall be documented in a record.
- The coating shall be carried out on a minimum of two test pieces of the same type with a coating time for each test piece of 30 s. Here the torch shall be swung in and swung out at high speed using the shortest possible way. The swing-in shall not take place until the spray jet is fully formed and stabilised (see Figure 1).
- After each spray test the change in mass of the test pieces shall be determined and documented (see Annex C).
- The mass of the spray material required is calculated using the spray time and feed rate. The mass shall be documented (see Annex C).

STANDARDSISO.COM : Click to view the full PDF of ISO 17836:2004

**Key**

- Y Feed rate
- t Time
- a Torch position
- 1 Stabilisation
- 2 Swing in
- 3 on test piece
- 4 Swing out

**Figure 1 — Test procedure****6 Determination of deposition efficiency**

The calculation of the deposition efficiency shall be carried out for each individual test piece and the mean value calculated.

$$\eta_D = \frac{\Delta m_{tp}}{m_{sm}} \times 100\%$$

where

- $\eta_D$  deposition efficiency, in %;
- $\Delta m_{tp}$  mass difference of test piece, in g;
- $m_{sm}$  mass of spray material fed through, in g;  
(It is the product of feed rate, in g/min, and spray time, in s, divided by 60).

**7 Test report**

The test results shall be entered in the record (see Annex C). The mean value shall be calculated from the test results.

The test report for determining the deposition efficiency shall include the following minimum of information:

- a) type of spray equipment and gun;
- b) feed mechanism of spray material;
- c) type of spray process;

- d) relevant spray parameters depending on the spray process (see spray record number);
- e) type of test piece;
- f) preparation of test pieces;
- g) spray material depending on type of alloy in accordance with EN 1274 for powders or EN ISO 14919 for wires, rods and cords, as applicable;
- h) mean value of feed rate;
- i) mean value of deposition efficiency.

## **8 Designation**

The designation of the deposition efficiency for the pipe (A) or the plate (B) shall consist of the following parts:

- 1) Document number;
- 2) Test piece (A or B according to Annex A or B) with mean value of deposition efficiency in %.


EXAMPLE:                **EN ISO 17836 – A 50**

STANDARDSISO.COM : Click to view the full PDF of ISO 17836:2004

## Annex A (normative)

### Test piece – Pipe (A)

The test piece shall be traversed by the spray jet, whereby the surface to be coated is reduced by at least one spray jet width from the edges.



#### Key


$w$  Spray jet width

Figure A.1 — Pipe, 150 mm  $\times$  200 mm  $\times$  3 mm

**Annex B**  
(normative)

**Test piece – Plate (B)**

The test piece shall be traversed by the spray jet, whereby the surface to be coated is reduced by at least one spray jet width from the edges.



**Key**

w Spray jet width

**Figure B.1 — Plate, 300 mm × 300 mm × 1 mm**