
**Welding consumables — Covered
electrodes for manual metal arc
welding of non-alloy and fine grain
steels — Classification**

*Produits consommables pour le soudage — Électrodes enrobées pour
le soudage manuel à l'arc des aciers non alliés et des aciers à grains
fins — Classification*

STANDARDSISO.COM : Click to view the full PDF of ISO 2560:2020



STANDARDSISO.COM : Click to view the full PDF of ISO 2560:2020



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	vi
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Classification	2
5 Symbols and requirements	3
5.1 Symbol for the product/process	3
5.2 Symbols for strength and elongation of all-weld metal	3
5.3 Symbol for impact properties of all-weld metal	5
5.4 Symbol for the chemical composition of all-weld metal	5
5.5 Symbol for type of electrode covering	7
5.6 Symbol for condition of post-weld heat-treatment of all-weld metal	9
5.7 Symbol for electrode efficiency and type of current	10
5.8 Symbol for welding position	10
5.9 Symbol for diffusible hydrogen content of deposited metal	11
6 Mechanical tests	11
6.1 Preheating and interpass temperatures	12
6.2 Pass sequence	14
7 Chemical analysis	15
8 Fillet weld test	20
9 Rounding procedure	22
10 Retests	22
11 Technical delivery conditions	22
12 Examples of designation	23
Annex A (informative) Classification systems	25
Annex B (informative) Description of types of electrode covering — Classification by yield strength and 47 J impact energy	28
Annex C (informative) Description of types of electrode covering — Classification by tensile strength and 27 J impact energy	30
Annex D (informative) Notes on diffusible hydrogen and the avoidance of cold cracking	33
Bibliography	34

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 3, *Welding consumables*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 121, *Welding and allied processes*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Official interpretations of ISO/TC 44 documents, where they exist, are available from this page: <https://committee.iso.org/sites/tc44/home/interpretation.html>.

This fourth edition cancels and replaces the third edition (ISO 2560:2009), which has been technically revised.

The main changes compared to the previous edition are as follows:

- all the references have been updated;
- throughout the document, “nominal electrode efficiency” now reads “electrode efficiency”;
- in 4B, “strength” has been clarified by changing to “tensile strength”;
- in Table 3B, the “Nominal level” for Mn shown in the 1st row of the table for “No symbol, -1, -P1, or -P2” was changed to 1,3;
- in Table 3B, a new footnote has been added regarding G classifications (similar to Table 3A);
- in Table 4B, a new footnote d to symbol “45” was added “Not including PF (vertical up)”;
- in [Table 8B](#), the heading of the last column has been revised to read “Impact test temperature”;
- in [Table 8B](#), NS (not specified) has been changed to NR (not required) and a new footnote c regarding testing at lower temperatures has been added;

- in [Table 10B](#), E4918, E4918-1, E5516-3M3, E5516-N3 and E5516-N7 have been updated to match values in AWS standards;
- in [Clause 8](#), *b* has been changed to *w* for width in accordance with ISO 15792-1;
- in [Clause 9](#), Rounding procedure has been updated to match current agreed wording;
- in Clause 12B, Example 1B, the %Mn was changed to 0,90 to better match the designation given in the example;

STANDARDSISO.COM : Click to view the full PDF of ISO 2560:2020

Introduction

This document recognizes that there are two somewhat different approaches in the global market to classifying a given electrode, and allows for either or both to be used, to suit a particular market need. Application of either type of classification designation (or of both, where suitable) identifies a product as classified in accordance with this document. The classification in accordance with system A is mainly based on EN 499:1994. The classification in accordance with system B is mainly based on standards used around the Pacific Rim.

This document provides a classification in order to designate covered electrodes in terms of the yield strength, tensile strength and elongation of the all-weld metal. The ratio of yield strength to tensile strength of weld metal is generally higher than that of parent metal. Users should note that matching weld metal yield strength to parent metal yield strength does not necessarily ensure that the weld metal tensile strength matches that of the parent metal. Therefore, where the application requires matching tensile strength, selection of the consumable should be made by reference to column 3 of Table 1A or to Table 1B and [Table 8B](#).

It should be noted that the mechanical properties of all-weld metal test specimens used to classify the electrodes vary from those obtained in production joints because of differences in welding procedure such as electrode size, width of weave, welding position, welding current, interpass temperature and parent metal composition.

STANDARDSISO.COM : Click to view the full PDF of ISO 2560:2020

Welding consumables — Covered electrodes for manual metal arc welding of non-alloy and fine grain steels — Classification

1 Scope

This document specifies requirements for the classification of covered electrodes and deposited metal in the as-welded condition and in the post-weld heat-treated condition for manual metal arc welding of non-alloy and fine grain steels with a minimum yield strength of up to 500 MPa or a minimum tensile strength of up to 570 MPa.

This document is a combined specification providing for classification utilizing a system based on the yield strength and the average impact energy of 47 J of all-weld metal, or utilizing a system based on the tensile strength and the average impact energy of 27 J of all-weld metal.

- a) Clauses, subclauses and tables which carry the suffix letter “A” are applicable only to covered electrodes classified to the system based on the yield strength and the average impact energy of 47 J of all weld metal in this document.
- b) Clauses, subclauses and tables which carry the suffix letter “B” are applicable only to covered electrodes classified to the system based on the tensile strength and the average impact energy of 27 J of all weld metal in this document.
- c) Clauses, subclauses and tables which do not have either the suffix letter “A” or the suffix letter “B” are applicable to all covered electrodes classified in this document.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 544, *Welding consumables — Technical delivery conditions for filler materials and fluxes — Type of product, dimensions, tolerances and markings*

ISO 2401, *Covered electrodes — Determination of the efficiency, metal recovery and deposition coefficient*

ISO 3690, *Welding and allied processes — Determination of hydrogen content in arc weld metal*

ISO 6847, *Welding consumables — Deposition of a weld metal pad for chemical analysis*

ISO 6947:2019, *Welding and allied processes — Welding positions*

ISO 14344, *Welding consumables — Procurement of filler materials and fluxes*

ISO 15792-1:2020, *Welding consumables — Test methods — Part 1: Test methods for all-weld metal test specimens in steel, nickel and nickel alloys*

ISO 15792-3:2011, *Welding consumables — Test methods — Part 3: Classification testing of positional capacity and root penetration of welding consumables in a fillet weld*

ISO 80000-1:2009, *Quantities and units — Part 1: General*. Corrected by ISO 80000-1:2009/Cor 1:2011

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

4 Classification

Classification designations are based on two approaches to indicate the tensile properties and the impact properties of the all-weld metal obtained with a given electrode. The two designation approaches include additional designators for some other classification requirements, but not all. In most cases, a given commercial product can be classified in both systems. Then, either or both classification designations can be used for the product.

The classification includes all-weld metal properties obtained with a covered electrode as given below. The classification is based on an electrode size of 4,0 mm, with the exception of the symbol for welding position, which is based on ISO 15792-3. Where the defined diameter has not been manufactured, the closest diameter to 4,0 mm shall be used for all-weld metal tests.

4A Classification by yield strength and 47 J impact energy

The classification is divided into eight parts:

- 1) the first part gives a symbol indicating the product/process to be identified;
- 2) the second part gives a symbol indicating the strength and elongation of all-weld metal (see Table 1A);
- 3) the third part gives a symbol indicating the impact properties of all-weld metal (see Table 2A);
- 4) the fourth part gives a symbol indicating the chemical composition of all-weld metal (see Table 3A);
- 5) the fifth part gives a symbol indicating the type of electrode covering (see 5.5A);
- 6) the sixth part gives a symbol indicating the electrode efficiency and type of current (see Table 5A);
- 7) the seventh part gives a symbol indicating the welding position (see Table 6A);
- 8) the eighth part gives a symbol indicating the diffusible hydrogen content of the deposited metal (see [Table 7](#)).

4B Classification by tensile strength and 27 J impact energy

The classification is divided into seven parts:

- 1) the first part gives a symbol indicating the product/process to be identified;
- 2) the second part gives a symbol indicating the tensile strength of all-weld metal (see Table 1B);
- 3) the third part gives a symbol indicating the type of electrode covering, the type of current, and the welding position (see Table 4B);
- 4) the fourth part gives a symbol indicating the chemical composition of all-weld metal (see Table 3B);
- 5) the fifth part gives a symbol indicating the condition of post-weld heat treatment under which the all-weld metal test was conducted (see 5.6B);
- 6) the sixth part gives a symbol indicating that the electrode has satisfied a requirement for 47 J impact energy at the temperature normally used for the 27 J requirement;
- 7) the seventh part gives a symbol indicating the diffusible hydrogen content of the deposited metal (see [Table 7](#)).

In order to promote the use of this document, the classification is split into two sections:

a) Compulsory section

This section includes the symbols for the type of product, the strength and elongation, the impact properties, the chemical composition and the type of covering, i.e. the symbols defined in 5.1, 5.2A, 5.3A, 5.4A and 5.5A.

b) Optional section

This section includes the symbols for the electrode efficiency, the type of current, the welding positions for which the electrode is suitable, and the symbol for diffusible hydrogen content, i.e. the symbols defined in 5.7A, 5.8A and 5.9.

The designation (see [Clause 12](#)), compulsory section and any chosen elements of the optional section, shall be used on packages and in the manufacturer's literature and data sheets. [Figure A.1](#) gives a schematic representation of the full designation of electrodes classified by yield strength and 47 J impact energy (system A). [Figure A.2](#) gives a schematic representation of the full designation of electrodes classified by tensile strength and 27 J impact energy (system B).

In order to promote the use of this document, the classification is split into two sections:

a) Compulsory section

This section includes the symbols for the type of product, the strength, the type of covering, the type of current, the welding position, the chemical composition and the condition of heat treatment, i.e. the symbols defined in 5.1, 5.2B, 5.4B, 5.5B and 5.6B.

b) Optional section

This section includes the symbol for the optional supplemental designator for 47 J impact energy, i.e. the symbol defined in 5.3B; and the symbol for diffusible hydrogen content, i.e., the symbol defined in 5.9.

5 Symbols and requirements

5.1 Symbol for the product/process

The symbol for the covered electrode used in the manual metal arc welding process shall be the letter E placed at the beginning of the designation.

5.2 Symbols for strength and elongation of all-weld metal

5.2A Classification by yield strength and 47 J impact energy

The symbols in Table 1A indicate the yield strength, tensile strength, and elongation of the all-weld metal in the as-welded condition, determined in accordance with [Clause 6](#).

5.2B Classification by tensile strength and 27 J impact energy

The symbols in Table 1B indicate the tensile strength of the all-weld metal in the as-welded condition or in the post-weld heat-treated condition, determined in accordance with [Clause 6](#). The yield strength and elongation requirements depend on the specific chemical composition, heat treatment condition and coating type, as well as on the tensile strength requirements, as given for the complete classification in [Table 8B](#).

Table 1A — Symbol for strength and elongation of all-weld metal

(Classification by yield strength and 47 J impact energy)

Symbol	Minimum yield strength ^a MPa	Tensile strength MPa	Minimum elongation ^b %
35	355	440 to 570	22
38	380	470 to 600	20
42	420	500 to 640	20
46	460	530 to 680	20
50	500	560 to 720	18

^a For yield strength, the lower yield strength (R_{eL}) shall be used when yielding occurs. Otherwise, the 0,2 % proof strength ($R_{p0,2}$) shall be used.

^b The gauge length is equal to five times the specimen diameter.

Table 1B — Symbol for strength of all-weld metal

(Classification by tensile strength and 27 J impact energy)

Symbol	Minimum tensile strength MPa
43	430
49	490
55	550
57	570

5.3 Symbol for impact properties of all-weld metal

5.3A Classification by yield strength and 47 J impact energy

The symbols in Table 2A indicate the temperature at which an average impact energy of 47 J is achieved under the conditions given in [Clause 6](#). Three specimens shall be tested. Only one individual value may be lower than 47 J but not lower than 32 J. When an all-weld metal has been classified for a certain temperature, it automatically covers any higher temperature in Table 2A.

Table 2A — Symbol for impact properties of all-weld metal
(Classification by yield strength and 47 J impact energy)

Symbol	Temperature for minimum average impact energy of 47 J °C
Z	No requirement
A	+20
0	0
2	−20
3	−30
4	−40
5	−50
6	−60

5.3B Classification by tensile strength and 27 J impact energy

There is no specific symbol for impact properties. The complete classification in [Table 8B](#) determines the temperature at which an impact energy of 27 J is achieved in the as-welded condition or in the post-weld heat-treated condition under the conditions given in [Clause 6](#). Five test specimens shall be tested. The lowest and highest values obtained shall be disregarded. Two of the three remaining values shall be greater than the specified 27 J level, one of the three may be lower but shall not be less than 20 J. The average of the three remaining values shall be at least 27 J.

The addition of the optional symbol U, immediately after the symbol for condition of heat treatment, indicates that the supplemental requirement of 47 J impact energy at the normal 27 J impact test temperature has also been satisfied. For the 47 J impact requirement, the number of specimens tested and values obtained shall meet the requirement of 5.3A.

5.4 Symbol for the chemical composition of all-weld metal

5.4A Classification by yield strength and 47 J impact energy

The symbols in Table 3A indicate the chemical composition of all-weld metal, determined in accordance with [Clause 7](#).

5.4B Classification by tensile strength and 27 J impact energy

The symbols in Table 3B indicate the principal alloying elements, and sometimes the nominal alloy level of the most significant alloy element, of all-weld metal, determined in accordance with [Clause 7](#). The symbol for chemical composition does not immediately follow the symbol for strength but follows the symbol for coating type. The complete classification, given in [Table 10B](#), determines the exact chemical composition requirements for a particular electrode classification.

Table 3A — Symbol for chemical composition of all-weld metal
(Classification by yield strength and 47 J impact energy)

Alloy symbol	Chemical composition % (by mass) ^{a,b,c}		
	Mn	Mo	Ni
No symbol	2,0	—	—
Mo	1,4	0,3 to 0,6	—
MnMo	1,4 to 2,0	0,3 to 0,6	—
1Ni	1,4	—	0,6 to 1,2
Mn1Ni	1,4 to 2,0	—	0,6 to 1,2
2Ni	1,4	—	1,8 to 2,6
Mn2Ni	1,4 to 2,0	—	1,2 to 2,6
3Ni	1,4	—	2,6 to 3,8
1NiMo	1,4	0,3 to 0,6	0,6 to 1,2
Z ^c	Any other agreed composition		

^a If not specified, Mo < 0,2; Ni < 0,3; Cr < 0,2; V < 0,05; Nb < 0,05; Cu < 0,3.

^b Single values shown in the table mean maximum values.

^c Consumables for which the chemical composition is not listed in the table shall be symbolized similarly and prefixed by the letter Z. The chemical composition ranges are not specified and therefore two electrodes with the same Z-classification may not be interchangeable.

Table 3B — Symbol for chemical composition of all-weld metal
(Classification by tensile strength and 27 J impact energy)

Alloy symbol	Chemical composition	
	Principal alloy element(s)	Nominal level % (by mass)
No symbol, -1, -P1 or -P2	Mn	1,3
-1M3	Mo	0,5
-3M2	Mn	1,5
	Mo	0,4
-3M3	Mn	1,5
	Mo	0,5
-N1	Ni	0,5
-N2	Ni	1,0
-N3	Ni	1,5
-3N3	Mn	1,5
	Ni	1,5
-N5	Ni	2,5
-N7	Ni	3,5
-N13	Ni	6,5
-N2M3	Ni	1,0
	Mo	0,5
-NC	Ni	0,5
	Cu	0,4
-CC	Cr	0,5
	Cu	0,4
-NCC	Ni	0,2
	Cr	0,6
	Cu	0,5
-NCC1	Ni	0,6
	Cr	0,6
	Cu	0,5
-NCC2	Ni	0,3
	Cr	0,2
	Cu	0,5
-G ^a	Any other agreed composition	

^a The chemical composition ranges are not specified and therefore two electrodes with the same G-classification may not be interchangeable.

5.5 Symbol for type of electrode covering

5.5A Classification by yield strength and 47 J impact energy

The type of covering of a covered electrode depends substantially on the types of slag-forming components. The symbols indicating the covering type shall be in accordance with Table 4A.

5.5B Classification by tensile strength and 27 J impact energy

The type of covering of a covered electrode depends substantially on the types of slag-forming components. The type of covering also determines the positions suitable for welding and the type of current, in accordance with Table 4B.

STANDARDSISO.COM : Click to view the full PDF of ISO 2560:2020

Table 4A — Symbol for type of covering
(Classification by yield strength and 47 J impact energy)

Symbol	Type of covering
A	Acid covering
C	Cellulosic covering
R	Rutile covering
RR	Rutile thick covering
RC	Rutile-cellulosic covering
RA	Rutile-acid covering
RB	Rutile-basic covering
B	Basic covering

NOTE A description of the characteristics of each of the types of covering is given in [Annex B](#).

Table 4B — Symbol for type of covering
(Classification by tensile strength and 27 J impact energy)

Symbol	Type of covering	Welding positions ^a	Type of current ^b
03	Rutile basic	All ^c	AC and DC (±)
10	Cellulosic	All	DC (+)
11	Cellulosic	All	AC and DC (+)
12	Rutile	All ^c	AC and DC (–)
13	Rutile	All ^c	AC and DC (±)
14	Rutile + iron powder	All ^c	AC and DC (±)
15	Basic	All ^c	DC (+)
16	Basic	All ^c	AC and DC (+)
18	Basic + iron powder	All ^c	AC and DC (+)
19	Ilmenite	All ^c	AC and DC (±)
20	Iron oxide	PA, PB	AC and DC (–)
24	Rutile + iron powder	PA, PB	AC and DC (±)
27	Iron oxide + iron powder	PA, PB	AC and DC (±)
28	Basic + iron powder	PA, PB, PC	AC and DC (+)
40	Not specified	Manufacturer's recommendations	
45	Basic	All ^d	DC (+)
48	Basic	All	AC and DC (+)

NOTE A description of the characteristics of each of the types of covering is given in [Annex C](#).

^a Positions in accordance with ISO 6947:2019. PA = flat, PB = horizontal vertical fillet, PC = horizontal, PG = vertical down.

^b Alternating current = AC; direct current = DC.

^c The indication “all positions” may or may not include vertical down welding. This shall be specified in the manufacturer's literature.

^d Not including PF (vertical up).

5.6 Symbol for condition of post-weld heat-treatment of all-weld metal

5.6A Classification by yield strength and 47 J impact energy

Classification is based on mechanical properties of the all-weld metal in the as-welded condition only. There is no symbol for condition of post-weld heat treatment.

5.6B Classification by tensile strength and 27 J impact energy

If the electrode has been classified in the as-welded condition, the symbol A shall be added to the classification. If the electrode has been classified in the post-weld heat-treated condition, the symbol P shall be added to the classification. When classified in the post-weld heat-treated condition, the temperature of post-weld heat treatment shall be $620\text{ }^{\circ}\text{C} \pm 15\text{ }^{\circ}\text{C}$, except for chemical compositions N5 and N7, where the temperature shall be $605\text{ }^{\circ}\text{C} \pm 15\text{ }^{\circ}\text{C}$, and chemical composition N13, where the temperature shall be $600\text{ }^{\circ}\text{C} \pm 15\text{ }^{\circ}\text{C}$. Post-weld heat treatment time shall be $60\text{ }^{(+15)}_0\text{ min}$ at temperature. If the electrode has been classified in both conditions, the symbol AP shall be added to the classification.

The furnace shall be at a temperature not higher than $300\text{ }^{\circ}\text{C}$ when the test assembly is placed in it. The heating rate, from that point to the specified holding temperature, shall be $85\text{ }^{\circ}\text{C}$ to $275\text{ }^{\circ}\text{C/h}$. When the holding time has been completed, the assembly shall be allowed to cool in the furnace to a temperature below $300\text{ }^{\circ}\text{C}$ at a rate not exceeding $200\text{ }^{\circ}\text{C/h}$. The assembly may be removed from the furnace at any temperature below $300\text{ }^{\circ}\text{C}$ and allowed to cool in still air to room temperature.

STANDARDSISO.COM : Click to view the full PDF of ISO 2560:2020

5.7 Symbol for electrode efficiency and type of current

5.7A Classification by yield strength and 47 J impact energy

The symbols in Table 5A indicate electrode efficiency, determined in accordance with ISO 2401 with the type of current shown in Table 5A.

5.7B Classification by tensile strength and 27 J impact energy

There is no specific symbol for electrode efficiency and type of current. Type of current is included in the symbol for type of covering (Table 4B). Electrode efficiency is not addressed.

Table 5A — Symbol for electrode efficiency and type of current
(Classification by yield strength and 47 J impact energy)

Symbol	Electrode efficiency, η , %	Type of current ^{a,b}
1	$\eta \leq 105$	AC and DC
2	$\eta \leq 105$	DC
3	$105 < \eta \leq 125$	AC and DC
4	$105 < \eta \leq 125$	DC
5	$125 < \eta \leq 160$	AC and DC
6	$125 < \eta \leq 160$	DC
7	$\eta > 160$	AC and DC
8	$\eta > 160$	DC

^a If an electrode is suitable for both DC and AC operation, the electrode efficiency shall be based on AC testing only.

^b Alternating current = AC; direct current = DC.

5.8 Symbol for welding position

5.8A Classification by yield strength and 47 J impact energy

The symbols in Table 6A for welding positions indicate the positions for which the electrode is tested in accordance with ISO 15792-3. For testing requirements (see [Clause 8](#)).

5.8B Classification by tensile strength and 27 J impact energy

There is no specific symbol for welding position. The welding position requirements are included with the symbol for type of covering (Table 4B).

Table 6A — Symbol for welding position
(Classification by yield strength and 47 J impact energy)

Symbol	Welding positions in accordance with ISO 6947:2019
1	PA, PB, PC, PD, PE, PF, PG
2	PA, PB, PC, PD, PE, PF
3	PA, PB
4	PA
5	PA, PB, PG

5.9 Symbol for diffusible hydrogen content of deposited metal

The symbols in [Table 7](#) indicate diffusible hydrogen content determined in deposited metal from an electrode of size 4 mm in accordance with the method given in ISO 3690. The current used shall be 70 % to 90 % of the maximum value recommended by the manufacturer. Electrodes recommended for use with AC and DC shall be tested using AC. Electrodes recommended for DC only shall be tested using DC with electrode positive.

The manufacturer shall provide information on the recommended type of current and redrying conditions for achieving the diffusible hydrogen levels.

Table 7 — Symbol for diffusible hydrogen content of deposited metal

Symbol	Diffusible hydrogen content maximum ml/100 g of deposited weld metal
H5	5
H10	10
H15	15

[Annex D](#) provides additional information about diffusible hydrogen.

6 Mechanical tests

6A Classification by yield strength and 47 J impact energy

Tensile and impact tests and any required retests shall be carried out in the as-welded condition using an all-weld metal test assembly type 1.3 in accordance with ISO 15792-1:2020 and the welding conditions described in [6.1](#) and [6.2](#).

6B Classification by tensile strength and 27 J impact energy

Tensile and impact tests and any required retests shall be carried out in the as-welded condition and/or in the post-weld heat-treated condition, using an all-weld metal test assembly type 1.3 in accordance with ISO 15792-1:2020 and the welding conditions described in [6.1](#) and [6.2](#).

When diffusible hydrogen removal treatment is specified by the manufacturer, it shall be carried out in accordance with ISO 15792-1.

6.1 Preheating and interpass temperatures

The preheating and interpass temperatures shall be measured using temperature indicator crayons, surface thermometers or thermocouples (for example, in accordance with ISO 13916).

6.1A Classification by yield strength and 47 J impact energy

Preheating is not required; welding may start from room temperature. The interpass temperature shall be in the range 90 °C to 175 °C. If, after any pass, the interpass temperature is exceeded, the test assembly shall be cooled in air to a temperature below that limit.

To reach tensile test requirements and impact properties at the same time, it can be necessary to keep the interpass temperature in a small range.

6.1B Classification by tensile strength and 27 J impact energy

Preheating and interpass temperature for electrodes with no chemical composition symbol or with the –1 symbol in Tables 3B and 8B shall be 100 °C to 150 °C. Preheating and interpass temperatures for all other compositions shall be 90 °C to 110 °C.

Table 8B — Mechanical test requirements
(Classification by tensile strength and 27 J impact energy)

Classification	Tensile strength ^a MPa	Yield strength ^a MPa	Elongation ^a A ₅ %	Impact test temperature ^{b,c} °C
E4303	430	330	20	0
E4310	430	330	20	–30
E4311	430	330	20	–30
E4312	430	330	16	NR
E4313	430	330	16	NR
E4316	430	330	20	–30
E4318	430	330	20	–30
E4319	430	330	20	–20
E4320	430	330	20	NR
E4324	430	330	16	NR
E4327	430	330	20	–30
E4340	430	330	20	0
E4903	490	400	20	0
E4910	490 to 650	400	20	–30
E4911	490 to 650	400	20	–30
E4912	490	400	16	NR
E4913	490	400	16	NR
E4914	490	400	16	NR
E4915	490	400	20	–30
E4916	490	400	20	–30
E4916-1	490	400	20	–45
E4918	490	400	20	–30
E4918-1	490	400	20	–45

^a Single values are minimum requirements.

^b NR = impact testing is not required.

^c Testing at a lower temperature is permitted but the requirements of 5.3B shall still be met.

Table 8B (continued)

Classification	Tensile strength ^a	Yield strength ^a	Elongation ^a A_5	Impact test temperature ^{b,c}
	MPa	MPa	%	°C
E4919	490	400	20	-20
E4924	490	400	16	NR
E4924-1	490	400	20	-20
E4927	490	400	20	-30
E4928	490	400	20	-20
E4948	490	400	20	-30
E5716	570	490	16	-30
E5728	570	490	16	-20
E4910-P1	490	420	20	-30
E5510-P1	550	460	17	-30
E5518-P2	550	460	17	-30
E5545-P2	550	460	17	-30
E4910-1M3	490	420	20	NR
E4911-1M3	490	400	20	NR
E4915-1M3	490	400	20	NR
E4916-1M3	490	400	20	NR
E4918-1M3	490	400	20	NR
E4919-1M3	490	400	20	NR
E4920-1M3	490	400	20	NR
E4927-1M3	490	400	20	NR
E5518-3M2	550	460	17	-50
E5516-3M3	550	460	17	-50
E5518-3M3	550	460	17	-50
E4916-N1	490	390	20	-40
E4928-N1	490	390	20	-40
E5516-N1	550	460	17	-40
E5528-N1	550	460	17	-40
E4916-N2	490	390	20	-40
E4918-N2	490	390	20	-50
E5516-N2	550	470 to 550	20	-40
E5518-N2	550	470 to 550	20	-40
E4916-N3	490	390	20	-40
E5516-N3	550	460	17	-50
E5516-3N3	550	460	17	-50
E5518-N3	550	460	17	-50
E4915-N5	490	390	20	-75
E4916-N5	490	390	20	-75
E4918-N5	490	390	20	-75
E4928-N5	490	390	20	-60

^a Single values are minimum requirements.

^b NR = impact testing is not required.

^c Testing at a lower temperature is permitted but the requirements of 5.3B shall still be met.

Table 8B (continued)

Classification	Tensile strength ^a	Yield strength ^a	Elongation ^a	Impact test temperature ^{b,c}
	MPa	MPa	A ₅ %	°C
E5516-N5	550	460	17	-60
E5518-N5	550	460	17	-60
E4915-N7	490	390	20	-100
E4916-N7	490	390	20	-100
E4918-N7	490	390	20	-100
E5516-N7	550	460	17	-75
E5518-N7	550	460	17	-75
E5516-N13	550	460	17	-100
E5518-N2M3	550	460	17	-40
E4903-NC	490	390	20	0
E4916-NC	490	390	20	0
E4928-NC	490	390	20	0
E5716-NC	570	490	16	0
E5728-NC	570	490	16	0
E4903-CC	490	390	20	0
E4916-CC	490	390	20	0
E4928-CC	490	390	20	0
E5716-CC	570	490	16	0
E5728-CC	570	490	16	0
E4903-NCC	490	390	20	0
E4916-NCC	490	390	20	0
E4928-NCC	490	390	20	0
E5716-NCC	570	490	16	0
E5728-NCC	570	490	16	0
E4903-NCC1	490	390	20	0
E4916-NCC1	490	390	20	0
E4928-NCC1	490	390	20	0
E5516-NCC1	550	460	17	-20
E5518-NCC1	550	460	17	-20
E5716-NCC1	570	490	16	0
E5728-NCC1	570	490	16	0
E4916-NCC2	490	420	20	-20
E4918-NCC2	490	420	20	-20
E49XX-G	490	400	20	NR
E55XX-G	550	460	17	NR
E57XX-G	570	490	16	NR

^a Single values are minimum requirements.

^b NR = impact testing is not required.

^c Testing at a lower temperature is permitted but the requirements of 5.3B shall still be met.

6.2 Pass sequence

The pass sequence shall be as indicated in [Table 9](#).

The direction of welding to complete a pass shall not vary. Each pass shall be executed with a welding current of 70 % to 90 % of the maximum current recommended by the manufacturer. Regardless of the type of covering, welding shall be performed with AC when both AC or DC are applicable and with DC using the recommended polarity when only DC is claimed.

Table 9 — Pass sequence

Electrode diameter ^a mm	Split weave		
	Layer No.	Passes per layer	Number of layers
4,0	1 to top	2 ^b	7 to 9

^a For diameters other than 4,0 mm, the pass sequence is to be specified by the manufacturer.

^b The top two layers may be completed with 3 passes per layer.

7 Chemical analysis

Chemical analysis may be performed on any suitable test piece, but in cases of dispute, specimens in accordance with ISO 6847 shall be used. Any analytical technique may be used, but in cases of dispute, reference shall be made to established published methods.

7A Classification by yield strength and 47 J impact energy

The results of the chemical analysis shall fulfil the requirements given in Table 3A.

7B Classification by tensile strength and 27 J impact energy

The results of the chemical analysis shall fulfil the requirements given in [Table 10B](#) for the classification under test.

Table 10B — All-weld metal deposit composition requirements
(Classification by tensile strength and 27 J impact energy)^{a,b}

Classification	Chemical composition % (by mass)										
	C	Mn	Si	P	S	Ni	Cr	Mo	V	Cu	Al
E4303	0,20	1,20	1,00	NS	NS	0,30	0,20	0,30	0,08	NS	NS
E4310	0,20	1,20	1,00	NS	NS	0,30	0,20	0,30	0,08	NS	NS
E4311	0,20	1,20	1,00	NS	NS	0,30	0,20	0,30	0,08	NS	NS
E4312	0,20	1,20	1,00	NS	NS	0,30	0,20	0,30	0,08	NS	NS
E4313	0,20	1,20	1,00	NS	NS	0,30	0,20	0,30	0,08	NS	NS
E4316	0,20	1,20	1,00	NS	NS	0,30	0,20	0,30	0,08	NS	NS
E4318	0,03	0,60	0,40	0,025	0,015	0,30	0,20	0,30	0,08	NS	NS
E4319	0,20	1,20	1,00	NS	NS	0,30	0,20	0,30	0,08	NS	NS
E4320	0,20	1,20	1,00	NS	NS	0,30	0,20	0,30	0,08	NS	NS
E4324	0,20	1,20	1,00	NS	NS	0,30	0,20	0,30	0,08	NS	NS
E4327	0,20	1,20	1,00	NS	NS	0,30	0,20	0,30	0,08	NS	NS
E4340	NS	NS	NS	NS	NS	NS	NS	NS	NS	NS	NS
E4903	0,15	1,25	0,90	NS	NS	0,30	0,20	0,30	0,08	NS	NS
E4910	0,20	1,25	0,90	0,035	0,035	0,30	0,20	0,30	0,08	NS	NS
E4911	0,20	1,25	0,90	0,035	0,035	0,30	0,20	0,30	0,08	NS	NS
E4912	0,20	1,20	1,00	NS	NS	0,30	0,20	0,30	0,08	NS	NS
E4913	0,20	1,20	1,00	NS	NS	0,30	0,20	0,30	0,08	NS	NS
E4914	0,15	1,25	0,90	0,035	0,035	0,30	0,20	0,30	0,08	NS	NS

^a Single values are maximum.

^b NS = Not specified.

Table 10B (continued)

Classification	Chemical composition % (by mass)										
	C	Mn	Si	P	S	Ni	Cr	Mo	V	Cu	Al
E4915	0,15	1,25	0,90	0,035	0,035	0,30	0,20	0,30	0,08	NS	NS
E4916	0,15	1,60	0,75	0,035	0,035	0,30	0,20	0,30	0,08	NS	NS
E4916-1	0,15	1,60	0,75	0,035	0,035	0,30	0,20	0,30	0,08	NS	NS
E4918	0,15	1,60	0,75	0,035	0,035	0,30	0,20	0,30	0,08	NS	NS
E4918-1	0,15	1,60	0,75	0,035	0,035	0,30	0,20	0,30	0,08	NS	NS
E4919	0,15	1,25	0,90	0,035	0,035	0,30	0,20	0,30	0,08	NS	NS
E4924	0,15	1,25	0,90	0,035	0,035	0,30	0,20	0,30	0,08	NS	NS
E4924-1	0,15	1,25	0,90	0,035	0,035	0,30	0,20	0,30	0,08	NS	NS
E4927	0,15	1,60	0,75	0,035	0,035	0,30	0,20	0,30	0,08	NS	NS
E4928	0,15	1,60	0,90	0,035	0,035	0,30	0,20	0,30	0,08	NS	NS
E4948	0,15	1,60	0,90	0,035	0,035	0,30	0,20	0,30	0,08	NS	NS
E5716	0,12	1,60	0,90	0,03	0,03	1,00	0,30	0,35	NS	NS	NS
E5728	0,12	1,60	0,90	0,03	0,03	1,00	0,30	0,35	NS	NS	NS
E4910-P1	0,20	1,20	0,60	0,03	0,03	1,00	0,30	0,50	0,10	NS	NS
E5510-P1	0,20	1,20	0,60	0,03	0,03	1,00	0,30	0,50	0,10	NS	NS
E5518-P2	0,12	0,90 to 1,70	0,80	0,03	0,03	1,00	0,20	0,50	0,05	NS	NS
E5545-P2	0,12	0,90 to 1,70	0,80	0,03	0,03	1,00	0,20	0,50	0,05	NS	NS
E4910-1M3	0,12	0,60	0,40	0,03	0,03	NS	NS	0,40 to 0,65	NS	NS	NS
E4911-1M3	0,12	0,60	0,40	0,03	0,03	NS	NS	0,40 to 0,65	NS	NS	NS
E4915-1M3	0,12	0,90	0,60	0,03	0,03	NS	NS	0,40 to 0,65	NS	NS	NS
E4916-1M3	0,12	0,90	0,60	0,03	0,03	NS	NS	0,40 to 0,65	NS	NS	NS
E4918-1M3	0,12	0,90	0,80	0,03	0,03	NS	NS	0,40 to 0,65	NS	NS	NS
E4919-1M3	0,12	0,90	0,40	0,03	0,03	NS	NS	0,40 to 0,65	NS	NS	NS
E4920-1M3	0,12	0,60	0,40	0,03	0,03	NS	NS	0,40 to 0,65	NS	NS	NS
E4927-1M3	0,12	1,00	0,40	0,03	0,03	NS	NS	0,40 to 0,65	NS	NS	NS
E5518-3M2	0,12	1,00 to 1,75	0,80	0,03	0,03	0,90	NS	0,25 to 0,45	NS	NS	NS
E5516-3M3	0,12	1,00 to 1,80	0,60	0,03	0,03	0,90	NS	0,40 to 0,65	NS	NS	NS
E5518-3M3	0,12	1,00 to 1,80	0,80	0,03	0,03	0,90	NS	0,40 to 0,65	NS	NS	NS
E4916-N1	0,12	0,60 to 1,60	0,90	0,03	0,03	0,30 to 1,00	NS	0,35	0,05	NS	NS
E4928-N1	0,12	0,60 to 1,60	0,90	0,03	0,03	0,30 to 1,00	NS	0,35	0,05	NS	NS
^a Single values are maximum.											
^b NS = Not specified.											

Table 10B (continued)

Classification	Chemical composition % (by mass)										
	C	Mn	Si	P	S	Ni	Cr	Mo	V	Cu	Al
E5516-N1	0,12	0,60 to 1,60	0,90	0,03	0,03	0,30 to 1,00	NS	0,35	0,05	NS	NS
E5528-N1	0,12	0,60 to 1,60	0,90	0,03	0,03	0,30 to 1,00	NS	0,35	0,05	NS	NS
E4916-N2	0,08	0,40 to 1,40	0,50	0,03	0,03	0,80 to 1,10	0,15	0,35	0,05	NS	NS
E4918-N2	0,08	0,40 to 1,40	0,50	0,03	0,03	0,80 to 1,10	0,15	0,35	0,05	NS	NS
E5516-N2	0,12	0,40 to 1,25	0,80	0,03	0,03	0,80 to 1,10	0,15	0,35	0,05	NS	NS
E5518-N2	0,12	0,40 to 1,25	0,80	0,03	0,03	0,80 to 1,10	0,15	0,35	0,05	NS	NS
E4916-N3	0,10	1,25	0,60	0,03	0,03	1,10 to 2,00	NS	0,35	NS	NS	NS
E5516-N3	0,10	1,25	0,60	0,03	0,03	1,10 to 2,00	NS	NS	NS	NS	NS
E5516-3N3	0,10	1,60	0,60	0,03	0,03	1,10 to 2,00	NS	NS	NS	NS	NS
E5518-N3	0,10	1,25	0,80	0,03	0,03	1,10 to 2,00	NS	NS	NS	NS	NS
E4915-N5	0,05	1,25	0,50	0,03	0,03	2,00 to 2,75	NS	NS	NS	NS	NS
E4916-N5	0,05	1,25	0,50	0,03	0,03	2,00 to 2,75	NS	NS	NS	NS	NS
E4918-N5	0,05	1,25	0,50	0,03	0,03	2,00 to 2,75	NS	NS	NS	NS	NS
E4928-N5	0,10	1,00	0,80	0,025	0,020	2,00 to 2,75	NS	NS	NS	NS	NS
E5516-N5	0,12	1,25	0,60	0,03	0,03	2,00 to 2,75	NS	NS	NS	NS	NS
E5518-N5	0,12	1,25	0,80	0,03	0,03	2,00 to 2,75	NS	NS	NS	NS	NS
E4915-N7	0,05	1,25	0,50	0,03	0,03	3,00 to 3,75	NS	NS	NS	NS	NS
E4916-N7	0,05	1,25	0,50	0,03	0,03	3,00 to 3,75	NS	NS	NS	NS	NS
E4918-N7	0,05	1,25	0,50	0,03	0,03	3,00 to 3,75	NS	NS	NS	NS	NS
E5516-N7	0,12	1,25	0,60	0,03	0,03	3,00 to 3,75	NS	NS	NS	NS	NS
E5518-N7	0,12	1,25	0,80	0,03	0,03	3,00 to 3,75	NS	NS	NS	NS	NS
E5516-N13	0,06	1,00	0,60	0,025	0,020	6,00 to 7,00	NS	NS	NS	NS	NS
E5518-N2M3	0,10	0,80 to 1,25	0,60	0,02	0,02	0,80 to 1,10	0,10	0,40 to 0,65	0,02	0,10	0,05
^a Single values are maximum. ^b NS = Not specified.											

Table 10B (continued)

Classification	Chemical composition % (by mass)										
	C	Mn	Si	P	S	Ni	Cr	Mo	V	Cu	Al
E4903-NC	0,12	0,30 to 1,40	0,90	0,03	0,03	0,25 to 0,70	0,30	NS	NS	0,20 to 0,60	NS
E4916-NC	0,12	0,30 to 1,40	0,90	0,03	0,03	0,25 to 0,70	0,30	NS	NS	0,20 to 0,60	NS
E4928-NC	0,12	0,30 to 1,40	0,90	0,03	0,03	0,25 to 0,70	0,30	NS	NS	0,20 to 0,60	NS
E5716-NC	0,12	0,30 to 1,40	0,90	0,03	0,03	0,25 to 0,70	0,30	NS	NS	0,20 to 0,60	NS
E5728-NC	0,12	0,30 to 1,40	0,90	0,03	0,03	0,25 to 0,70	0,30	NS	NS	0,20 to 0,60	NS
E4903-CC	0,12	0,30 to 1,40	0,90	0,03	0,03	NS	0,30 to 0,70	NS	NS	0,20 to 0,60	NS
E4916-CC	0,12	0,30 to 1,40	0,90	0,03	0,03	NS	0,30 to 0,70	NS	NS	0,20 to 0,60	NS
E4928-CC	0,12	0,30 to 1,40	0,90	0,03	0,03	NS	0,30 to 0,70	NS	NS	0,20 to 0,60	NS
E5716-CC	0,12	0,30 to 1,40	0,90	0,03	0,03	NS	0,30 to 0,70	NS	NS	0,20 to 0,60	NS
E5728-CC	0,12	0,30 to 1,40	0,90	0,03	0,03	NS	0,30 to 0,70	NS	NS	0,20 to 0,60	NS
E4903-NCC	0,12	0,30 to 1,40	0,90	0,03	0,03	0,05 to 0,45	0,45 to 0,75	NS	NS	0,30 to 0,70	NS
E4916-NCC	0,12	0,30 to 1,40	0,90	0,03	0,03	0,05 to 0,45	0,45 to 0,75	NS	NS	0,30 to 0,70	NS
E4928-NCC	0,12	0,30 to 1,40	0,90	0,03	0,03	0,05 to 0,45	0,45 to 0,75	NS	NS	0,30 to 0,70	NS
E5716-NCC	0,12	0,30 to 1,40	0,90	0,03	0,03	0,05 to 0,45	0,45 to 0,75	NS	NS	0,30 to 0,70	NS
E5728-NCC	0,12	0,30 to 1,40	0,90	0,03	0,03	0,05 to 0,45	0,45 to 0,75	NS	NS	0,30 to 0,70	NS
E4903-NCC1	0,12	0,50 to 1,30	0,35 to 0,80	0,03	0,03	0,40 to 0,80	0,45 to 0,70	NS	NS	0,30 to 0,75	NS
E4916-NCC1	0,12	0,50 to 1,30	0,35 to 0,80	0,03	0,03	0,40 to 0,80	0,45 to 0,70	NS	NS	0,30 to 0,75	NS
E4928-NCC1	0,12	0,50 to 1,30	0,80	0,03	0,03	0,40 to 0,80	0,45 to 0,70	NS	NS	0,30 to 0,75	NS
E5516-NCC1	0,12	0,50 to 1,30	0,35 to 0,80	0,03	0,03	0,40 to 0,80	0,45 to 0,70	NS	NS	0,30 to 0,75	NS
E5518-NCC1	0,12	0,50 to 1,30	0,35 to 0,80	0,03	0,03	0,40 to 0,80	0,45 to 0,70	NS	NS	0,30 to 0,75	NS
E5716-NCC1	0,12	0,50 to 1,30	0,35 to 0,80	0,03	0,03	0,40 to 0,80	0,45 to 0,70	NS	NS	0,30 to 0,75	NS
^a Single values are maximum. ^b NS = Not specified.											

Table 10B (continued)

Classification	Chemical composition % (by mass)										
	C	Mn	Si	P	S	Ni	Cr	Mo	V	Cu	Al
E5728-NCC1	0,12	0,50 to 1,30	0,80	0,03	0,03	0,40 to 0,80	0,45 to 0,70	NS	NS	0,30 to 0,75	NS
E4916-NCC2	0,12	0,40 to 0,70	0,40 to 0,70	0,025	0,025	0,20 to 0,40	0,15 to 0,30	NS	0,08	0,30 to 0,60	NS
E4918-NCC2	0,12	0,40 to 0,70	0,40 to 0,70	0,025	0,025	0,20 to 0,40	0,15 to 0,30	NS	0,08	0,30 to 0,60	NS
E49XX-G	NS	NS	NS	NS	NS	NS	NS	NS	NS	NS	NS
E55XX-G	NS	NS	NS	NS	NS	NS	NS	NS	NS	NS	NS
E57XX-G	NS	NS	NS	NS	NS	NS	NS	NS	NS	NS	NS
^a Single values are maximum. ^b NS = Not specified.											

8 Fillet weld test

The fillet weld test assembly shall be as shown in ISO 15792-3:2011, Figure 1.

8A Classification by yield strength and 47 J impact energy

The plate material shall be selected from the range of materials for which the electrode is recommended by the manufacturer. The surface shall be free of scale, rust and other contaminants. The test plate thickness, t , shall be 10 mm to 12 mm, the width, w , shall be 75 mm minimum and the length, l , shall be 300 mm minimum. The electrode sizes to be tested for each coating type, the test positions and the required test results are given in [Table 11A](#).

8B Classification by tensile strength and 27 J impact energy

The plate material shall be unalloyed steel of 0,30 % (by mass) C maximum. The surfaces to be welded shall be clean. The test plate thickness, t , shall be 10 mm to 12 mm in accordance with [Table 11B](#). The width, w , the length, l , the test positions for each coating type, and the required test results are given in [Tables 11B](#) and [12B](#).

Table 11A — Test requirements for fillet welds^a
(Classification by yield strength and 47 J impact energy)

Dimensions in millimetres

Symbol of position for classification	Coating type	Test position	Electrode size ^a	Fillet theoretical throat	Leg length difference	Convexity
1 or 2	C	PB	6,0	4,5 min.	1,5 max.	2,5 max.
	RX ^b			5,0 min.	2,0 max.	3,0 max.
	B			5,0 min.	2,0 max.	3,0 max.
3	A	PB	6,0	5,0 min.	2,0 max.	3,0 max.
	RR					
5	R	PB	6,0	4,5 min.	1,5 max.	2,5 max.
	B		5,0			
1 or 2	C	PF	4,0	4,5 max.	—	2,0 max.
	RX ^b			4,5 max.		
	B			5,5 max.		
1 or 2	C	PD	4,0	4,5 max.	1,5 max.	2,5 max.
	RX ^b			4,5 max.	1,5 max.	2,5 max.
	B			5,5 max.	2,0 max.	3,0 max.
5	B	PG	4,0	5,0 min.	—	1,5 max. ^c

^a Where the largest size claimed for positional welding is smaller than that specified, use the largest size and adjust criteria pro rata. Otherwise, electrode sizes not shown are not required to be tested.

^b RX includes R, RC, RA and RB.

^c Maximum concavity.

Table 11B — Test requirements for fillet welds
(Classification by tensile strength and 27 J impact energy)

Coating type	Current and polarity	Electrode size ^a	Test position	Minimum plate width <i>w</i>	Minimum plate length <i>l</i>	Fillet weld size
03	AC and DC (+)	5,0 6,0	PF, PD PB	75	300 400	10,0 max. 8,0 min.
10	DC (+)	5,0 6,0	PF, PD PB	75	300 400	8,0 max. 6,0 min.
11	AC and DC (+)	5,0 6,0	PF, PD PB	75	300 400	8,0 max. 6,0 min.
12	AC and DC (-)	5,0 6,0	PF, PD PB	75	300 400	10,0 max. 8,0 min.
13	AC, DC (-) and DC (+)	5,0 6,0	PF, PD PB	75	300 400	10,0 max. 8,0 min.
14	AC, DC (-) and DC (+)	4,0 6,0	PF, PD PB	75	300 400	8,0 max. 8,0 min.
15	DC (+)	4,0 6,0	PF, PD PB	75	300 400	8,0 max. 8,0 min.
16	AC and DC (+)	4,0 6,0	PF, PD PB	75	300 400	8,0 max. 8,0 min.
18	AC and DC (+)	4,0 6,0	PF, PD PB	75	300 400	8,0 max. 8,0 min.
19	AC and DC (+)	5,0 6,0	PF, PD PB	75	300 400	10,0 max. 8,0 min.
20	AC and DC (-)	6,0	PB	75	400	8,0 min.
24	AC, DC (-) and DC (+)	6,0	PB	75	400 or 650 ^b	8,0 min.
27	AC and DC (-)	6,0	PB	75	400 or 650 ^b	8,0 min.
28	AC and DC (+)	6,0	PB	75	400 or 650 ^b	8,0 min.
40	NS ^c	NS ^c	NS ^c	75	NS ^c	NS ^c
45	DC (+)	4,0 4,5	PE, PG	75	300	8,0 max. 6,0 min.
48	AC and DC (+)	4,0 5,0	PD, PG PB, PG	75	300 300 or 400 ^d	8,0 max. 6,5 min.

^a Where the largest size claimed for positional welding is smaller than that specified, use the largest size and adjust criteria pro rata. Otherwise, electrode sizes not shown are not required to be tested.

^b For 450 mm electrode length, *l* shall be 400 minimum. For 700 mm electrode length, *l* shall be 650 mm minimum.

^c NS = Not specified. Requirements shall be agreed between purchaser and supplier.

^d For 350 mm electrode length, *l* shall be 300 mm minimum. For 450 mm or 460 mm electrode length, *l* shall be 400 mm minimum.

Table 12B — Allowable leg length difference and maximum convexity

Dimensions in millimetres

Measured fillet weld size	Maximum leg length difference	Maximum convexity
4,0 or less	1,0	2,0
4,5	1,5	2,0
5,0 or 5,5	2,0	2,0
6,0 or 6,5	2,5	2,0
7,0, 7,5 or 8,0	3,0	2,5
8,5	3,5	2,5
9,0 or more	4,0	2,5

9 Rounding procedure

Actual test values obtained shall be subject to ISO 80000-1:2009, B.3, Rule A. If the measured values are obtained by equipment calibrated in units other than those of this document, the measured values shall be converted to the units of this document before rounding. If an average value is to be compared to the requirements of this document, rounding shall be done only after calculating the average. The rounded results shall fulfil the requirements of the appropriate table for the classification under test.

10 Retests

If any test fails to meet the requirement(s), that test shall be repeated twice. The results of both retests shall meet the requirement. Specimens for the retest may be taken from the original test assembly or sample or from one or two new test assemblies. For chemical analysis, retests are only needed for those specific elements that failed to meet the requirement. If the results of one or both retests fail to meet the requirement, the material under test shall be considered as not meeting the requirements of this document for that classification.

In the event that during preparation, or after completion of any test, it is clearly determined that prescribed or proper procedures were not followed in preparing the weld test assembly or sample(s) or test specimen(s), or in conducting the tests, the test shall be considered invalid. This determination is made without regard to whether the test was actually completed, or whether the test results met, or failed to meet, the requirements. That test shall be repeated, following proper prescribed procedures. In this case, the requirement for doubling the number of test specimens does not apply.

11 Technical delivery conditions

Technical delivery conditions shall meet the requirements in ISO 544 and in ISO 14344.

12 Examples of designation

12A Classification by yield strength and 47 J impact energy

The designation of the covered electrode is indicated by the suffix letter A given after the number of this document and shall follow the principles given in the example below.

EXAMPLE 1A:

A covered electrode for manual metal arc welding which deposits a weld metal with a minimum yield strength of 460 MPa (46) and a minimum average impact energy of 47 J at –30 °C (3) with a chemical composition of 1,1 % (by mass) Mn and 0,7 % (by mass) Ni (1Ni) having a basic covering (B) and a electrode efficiency of 140 % and which may be used with AC and DC (5) in flat butt and flat fillet welds (3) and whose diffusible hydrogen content is determined in accordance with ISO 3690 and does not exceed 5 ml/100 g of deposited metal (H5) is designated as follows:

ISO 2560-A-E 46 3 1Ni B 5 3 H5

Compulsory section:

ISO 2560-A-E 46 3 1Ni B

where

ISO 2560-A	is the number of this document, classification by yield strength and 47 J impact energy;
E	is the covered electrode/manual metal arc welding (see 4.1);
46	is the strength and elongation (see Table 1A);
3	are the impact properties (see Table 2A);

12B Classification by tensile strength and 27 J impact energy

The designation of the covered electrode is indicated by the suffix letter B given after the number of this document and shall follow the principles given in the example below.

EXAMPLE 1B:

A covered electrode for manual metal arc welding which deposits a weld metal with a minimum tensile strength of 550 MPa (55) and which meets a 47 J impact requirement at –40 °C (U) in the as-welded condition and also exceeds 27 J at –40 °C in the as-welded condition (A) with a chemical composition of 0,9 % (by mass) Mn and 1 % (by mass) Ni (–N2) having a basic covering including iron powder and which may be used with AC and DC (+) in all positions except vertical down (18) and whose diffusible hydrogen content is determined in accordance with ISO 3690 and does not exceed 5 ml/100 g of deposited metal (H5) is designated as follows:

ISO 2560-B-E5518-N2A U H5

Compulsory section:

ISO 2560-B-E5518-N2A

where

ISO 2560-B	is the number of this document, classification by tensile strength and 27 J impact energy;
E	is the covered electrode/manual metal arc welding (see 4.1);
55	is the tensile strength (see Table 1B);

B	is the type of electrode covering (see Table 4A);	18	is the basic iron powder coating suitable for AC and DC (+), in all positions except vertical down (see Table 4B);
5	is the electrode efficiency and type of current (see Table 5A);	–N2	is the 1 % (by mass) Ni as the principal alloying element (see Table 3B);
3	is the welding position (see Table 6A);	E5518-N2 A	is the complete specification of composition limits and mechanical property requirements (see Tables 8B and 10B) in the as-welded condition;
H5	is the diffusible hydrogen content (see Table 7).	U	is the supplemental impact requirement of 47 J at the basic 27 J impact test temperature;
		H5	is the diffusible hydrogen content (see Table 7).

Annex A

(informative)

Classification systems


A.1 ISO 2560-A

The ISO 2560-A classification system for covered electrodes for non-alloy and fine grain steels, based on yield strength and 47 J minimum impact energy, is shown in [Figure A.1](#).

A.2 ISO 2560-B

The ISO 2560-B classification system for covered electrodes for non-alloy and fine grain steels, based on tensile strength and 27 J minimum impact energy, is shown in [Figure A.2](#).

STANDARDSISO.COM : Click to view the full PDF of ISO 2560:2020


Compulsory classification designators^a**Optional supplemental designators^b**

- Optional supplemental diffusible hydrogen designator. "H5, H10 or H15" is used to indicate a maximum diffusible hydrogen content of 5 ml/100 g, 10 ml/100 g or 15 ml/100 g of deposited metal, respectively.
- Positionality designator. The symbol "1, 2, 3, 4 or 5" indicates the welding position(s) for which the electrode is suitable.
- Metal recovery and type of current indicator. The symbol "1, 2, 3, 4, 5, 6, 7 or 8" indicates the weld metal recovery and type of current.

^a The combination of these designators constitutes the covered electrode classification.

^b These designators are optional and do not constitute part of the covered electrode classification.

Figure A.1 — ISO 2560-A designation of electrodes
(Classification by yield strength and 47 J impact energy)

Compulsory classification designators^a**Optional supplemental designators^b**

- Optional supplemental diffusible hydrogen designator. "H5, H10 or H15" is used to indicate a maximum diffusible hydrogen content of 5 ml/100 g, 10 ml/100 g or 15 ml/100 g of deposited metal, respectively.
- Optional supplemental designator to indicate 47 J impact energy at the normal 27 J test temperature.

^a The combination of these designators constitutes the covered electrode classification.

^b These designators are optional and do not constitute part of the covered electrode classification.

Figure A.2 — ISO 2560-B designation of electrodes
(Classification by tensile strength and 27 J impact energy)