

# AEROSPACE MATERIAL SPECIFICATION



**AMS 3430C**

Issued JAN 1958  
Revised OCT 2001  
Reaffirmed APR 2006

Superseding AMS 3430B

(R)

## Brazing Filler Metal, Paste, Copper Water Thinning

### 1. SCOPE:

#### 1.1 Form:

This specification covers a copper brazing filler metal in the form of a paste comprising a viscous mixture of powder in a suitable binder.

#### 1.2 Application:

This product has been used typically for joining carbon and low-alloy steels and corrosion and heat resistant steels and alloys where high strength, good ductility, and only short-time oxidation resistance above 1000 °F (538 °C) are required, but usage is not limited to such applications. Used where inserts of copper wire or sheet are impractical and where carburization of the metals being joined is undesirable.

#### 1.3 Classification:

The brazing filler metal pastes covered by this specification are classified as follows:

Type 1: The active ingredient is composed of cupric and cuprous oxides and metallic copper.

Type 2: The active ingredient is composed of metallic copper.

- 1.4 Safety - Hazardous Materials: While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2006 SAE International

All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:

TO PLACE A DOCUMENT ORDER:

SAE WEB ADDRESS:

(724) 772-7161

(724) 776-4970

<http://www.sae.org>

FAX: (724) 776-0243

FAX: (724) 776-0790

## 2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

### 2.1 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959 or <http://www.astm.org>.

ASTM B 214 Sieve Analysis of Granular Metal Powders  
ASTM E 478 Chemical Analysis of Copper Alloys

## 3. TECHNICAL REQUIREMENTS:

### 3.1 Composition:

#### 3.1.1 Paste shall conform to the requirements shown in Table 1.

TABLE 1—Composition of Paste

Material	Percent min	Percent max
Active ingredient	70.0	--
Vehicle	--	30.0

#### 3.1.2 Active Ingredient Composition: Shall conform to the following, determined by wet chemical methods in accordance with ASTM E 478, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

##### 3.1.2.1 Type 1: Shall be 97% cuprous oxide ( $\text{Cu}_2\text{O}$ ). The remainder shall be cupric oxide ( $\text{CuO}$ ) and copper metal powder.

##### 3.1.2.2 Type 2: Shall be 99.0% minimum metallic copper with not more than 0.03% other elements. The remainder may be copper oxide. Oxygen shall not be included with other elements in the analysis.

##### 3.1.2.3 Vehicle: Shall be a water based mixture containing organic additives for thickening such as ethylene glycol, algin, petroleum sulfonate, or other organic additives as required.

##### 3.1.2.4 Where no type is specified, Type 1 shall be supplied.

**3.2 Condition:**

Paste shall be supplied as mixed and shall not contain flux.

**3.3 Brazability:**

Paste shall be applied to a steel test panel, heated to  $2050^{\circ}\text{F} \pm 25$  ( $1121^{\circ}\text{C} \pm 14$ ) in a hydrogen atmosphere having a dew point not higher than  $-40^{\circ}\text{F}$  ( $-40^{\circ}\text{C}$ ), held at heat for 30 minutes  $\pm 2$ , and cooled to  $1000^{\circ}\text{F}$  ( $538^{\circ}\text{C}$ ) or lower in a protective atmosphere. The active ingredient shall be reduced completely to metallic copper and shall melt and flow freely. The vehicle and emulsifying agent shall burn off leaving no carbonaceous residue and shall not cause carburization of the panel.

**3.4 Shelf Life:**

Shall be not less than six months from date of shipment when paste is stored in manufacturer's sealed containers; not more than thorough mixing shall be required to restore paste for use during that time.

**3.5 Quality:**

Paste, as received by purchaser, shall be uniform in quality and condition and free from foreign materials and from imperfections detrimental to usage of the product. Paste, diluted with water or other appropriate miscible solvent as required, shall have acceptable application characteristics.

**3.6 Sizes and Tolerances:**

The active ingredients shall be of such fineness that for Type 1, not more than 0.5% by weight shall be retained on a No. 325 (45  $\mu\text{m}$ ) screen, and for Type 2 not more than 10% by weight shall be retained on a No. 325 (45  $\mu\text{m}$ ) screen and not more than 0.5% shall be retained on a No. 200 ( $\mu$ ) screen, determined in accordance with ASTM B 214 or by other method acceptable to purchaser.

**4. QUALITY ASSURANCE PROVISIONS:****4.1 Responsibility for Inspection:**

The vendor of paste shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the paste conforms to specified requirements.

**4.2 Classification of Tests:**

**4.2.1 Acceptance Tests:** All technical requirements except shelf life are acceptance tests and shall be performed on each lot.

**4.2.2 Preproduction Tests:** Shelf life is a preproduction test and shall be performed prior to initial shipment of the product and after any change to the product (See 4.4).

#### 4.3 Sampling and Testing:

Shall be in accordance with the following; a lot shall be all paste produced from a single lot of powder combined with binder from the same manufacturing batch and presented for vendor's inspection at one time.

##### 4.3.1 Composition: One sample from each lot.

#### 4.4 Identification:

Product shall be assigned an identifying name, code, or revision letters or numbers traceable to a specific set and proportion of ingredients, raw materials, methods of manufacture and quality assurance methods. That identifying name, code, or revision letters or numbers shall be changed if there are any changes to the set and proportions of ingredients, raw materials, methods of manufacture, or quality assurance methods.

#### 4.5 Reports:

The vendor of paste shall furnish with each shipment a report showing the results of tests on each lot to determine conformance to the composition requirements and stating that the product conforms to the other technical requirements. This report shall include the purchase order number, manufacturer's identification, lot number, AMS 3430C, and quantity.

#### 4.6 Resampling and Retesting:

If any specimen used in the above tests fails to meet the specified requirements, disposition of the paste may be based on the results of testing three additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the paste represented. Results of all tests shall be reported.

### 5. PREPARATION FOR DELIVERY:

#### 5.1 Identification:

Each exterior container shall be permanently and legibly marked with not less than the following information:

AMS 3430C

TRADE NAME \_\_\_\_\_

VOLUME OF CONTENTS \_\_\_\_\_

DATE OF MANUFACTURE \_\_\_\_\_

LOT NUMBER \_\_\_\_\_

MANUFACTURER'S IDENTIFICATION (See 4.4) \_\_\_\_\_

DIRECTIONS FOR APPLICATION \_\_\_\_\_