



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc. 400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

AMS 5363C

Superseding AMS 5363B

Issued 12-1-47
Revised 4-15-78

UNS J92641

STEEL CASTINGS, SAND AND CENTRIFUGAL, CORROSION AND HEAT RESISTANT
18.5Cr - 10.5Ni - 0.90(Cb+Ta)

SAE Technical Board rules provide that: "All technical reports, including standards adopted and recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

1. SCOPE:

- 1.1 Form: This specification covers a corrosion and heat resistant steel in the form of sand or centrifugal castings.
- 1.2 Application: Primarily for parts requiring corrosion and heat resistance up to 800° F (425° C), especially when such parts are welded during fabrication, and for parts requiring oxidation resistance up to 1500° F (815° C) but useful at that temperature only when stresses are low.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

- AMS 2350 - Standards and Test Methods
AMS 2360 - Room Temperature Tensile Properties of Castings
AMS 2635 - Radiographic Inspection
AMS 2645 - Fluorescent Penetrant Inspection
AMS 2804 - Identification, Castings

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

- ASTM A262 - Detecting Susceptibility to Intergranular Attack in Stainless Steels
ASTM A370 - Mechanical Testing of Steel Products
ASTM E353 - Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys
ASTM E446 - Reference Radiographs for Steel Castings Up to 2 in. (51 mm) in Thickness

2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

- Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Standards:

- MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other approved analytical methods:

	min	max
Carbon	--	0.10
Manganese	--	2.00
Silicon	--	1.50
Phosphorus	--	0.04
Sulfur	--	0.04
Chromium	17.00 - 20.00	
Nickel	9.00 - 12.00	
Columbium + Tantalum	10xC - 1.35	
Molybdenum	--	0.75
Copper	--	0.75

- 3.2 Condition: Solution heat treated free from continuous carbide network.

- 3.3 Casting: A melt shall be the metal poured from a single furnace charge of 10 000 lb (4540 kg) or less.

- 3.4 Test Specimens: Chemical analysis specimens shall be of any convenient size, shape, and form for vendor's tests. When chemical analysis specimens are required by purchaser, specimens shall be cast to a size, shape, and form agreed upon by purchaser and vendor.

- 3.5 Heat Treatment: Castings shall be solution heat treated by heating to $1950^{\circ}\text{F} \pm 50$ ($1065^{\circ}\text{C} \pm 30$), holding at heat for 60 min. per inch (25 mm) of maximum cross-section but in no case less than 30 min., and cooling as necessary or desired.

- 3.6 Properties: Castings shall conform to the following requirements; hardness and tensile testing shall be performed in accordance with ASTM A370:

- 3.6.1 Hardness: Shall be not higher than 180 HB or equivalent.

- 3.6.2 Embrittlement: Specimens cut from castings, after sensitizing treatment, shall show no evidence of intercrystalline surface attack when examined microscopically after exposure to copper/copper sulfate/sulfuric acid test in accordance with ASTM A262, Practice E.

- 3.6.3 Tensile Properties: When specified on the drawing or when agreed upon by purchaser and vendor, tensile test specimens conforming to ASTM A370 shall be machined from castings selected at random from each melt. Property requirements for such specimens shall be as shown on the drawing or as agreed upon by purchaser and vendor and may be defined as specified in AMS 2360.

3.7 Quality:

- 3.7.1 Castings, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the castings.

- 3.7.1.1 Castings shall have smooth surfaces and shall be well cleaned. Metallic shot or grit shall not be used for final cleaning, unless otherwise permitted.

- 3.7.2 Castings shall be produced under radiographic control, unless otherwise specified. This control shall consist of radiographic examination of castings in accordance with AMS 2635 until proper foundry technique, which will produce castings free from harmful internal imperfections, is established for each part number and of production castings as necessary to ensure maintenance of satisfactory quality.
- 3.7.3 When specified, castings shall be subjected to fluorescent penetrant inspection in accordance with AMS 2645.
- 3.7.4 Radiographic, fluorescent penetrant, and other quality standards shall be as agreed upon by purchaser and vendor. ASTM E446 may be used to define radiographic acceptance standards.
- 3.7.5 Castings shall not be repaired by peening, plugging, welding, or other methods without written permission from purchaser.
- 3.7.5.1 When permitted in writing by purchaser, defects in castings may be removed and the castings repaired by welding provided the weld repair area has properties comparable to those of the parent metal. Repair welds shall be subjected to the same inspection procedures and acceptance standards required of the casting. Weld repair areas shall be suitably marked to facilitate inspection. The repair welding shall be performed prior to any heat treatment and nondestructive testing specified herein.

4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of castings shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to ensure that the castings conform to the requirements of this specification.
- 4.2 Classification of Tests:
- 4.2.1 Acceptance Tests: Tests to determine conformance to composition (3.1), hardness (3.6.1), quality (3.7), and, when specified, tensile property requirements of specimens cut from castings (3.6.3) are classified as acceptance tests.
- 4.2.2 Periodic Tests: Tests to determine conformance to embrittlement (3.6.2) requirements are classified as periodic tests.
- 4.2.3 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests.
- 4.2.3.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.
- 4.3 Sampling: Shall be in accordance with the following:
- 4.3.1 Two chemical analysis specimens in accordance with 3.4 and/or a casting from each melt.
- 4.3.2 Two preproduction castings in accordance with 4.4.1 of each part number.
- 4.3.3 One or more castings from each melt when properties of specimens machined from castings are required. Size, location, and number of specimens machined from castings shall be as specified on the drawing or as agreed upon by purchaser and vendor. When size, location, and number of specimens are not specified, not less than two tensile test specimens, one from the thickest section and one from the thinnest section, shall be cut from a casting or castings from each melt.

4.4 Approval:

- 4.4.1 Sample castings from new or reworked patterns or molds and the casting procedure shall be approved by purchaser before castings for production use are supplied, unless such approval be waived.
- 4.4.2 Vendor shall establish for production of sample castings of each part number the control factors of processing which will produce acceptable castings; these shall constitute the approved casting procedure and shall be used for producing production castings. If necessary to make any change in control factors of processing, vendor shall submit for reapproval a statement of the proposed changes in processing and, when requested, sample test specimens, castings, or both. Production castings incorporating the revised operations shall not be shipped prior to receipt of reapproval.

4.4.2.1 Control factors for producing castings include, but are not limited to, the following:

- Type of furnace and its capacity
Size of furnace charge
Furnace atmosphere
Fluxing or deoxidation procedure
Gating and risering practices
Pouring temperature (variation of $\pm 50^{\circ}\text{F}$ ($\pm 30^{\circ}\text{C}$) from the established limit is permissible)
Solidification and cooling procedures
Cleaning operations
Solution heat treatment cycle
Methods of routine inspection

- 4.4.2.1.1 Any of the above control factors of processing considered proprietary by the vendor may be assigned a code designation. Each variation in such factors shall be assigned a modified code designation.

4.5 Reports:

- 4.5.1 The vendor of castings shall furnish with each shipment three copies of a report showing the results of tests for chemical composition of each melt represented and stating that the castings conform to the other technical requirements of this specification. When properties of specimens cut from castings are specified, the report shall include the results of tests to determine conformance to such requirements. This report shall include the purchase order number, melt number, material specification number and its revision letter, part number, and quantity from each melt.
- 4.5.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number and its revision letter, contractor or other direct supplier of castings, part number, and quantity. When castings for making parts are produced or purchased by the parts vendor, that vendor shall inspect castings from each melt represented to determine conformance to the requirements of this specification, and shall include in the report a statement that the castings conform, or shall include copies of laboratory reports showing the results of tests to determine conformance.
- 4.6 Resampling and Retesting: If any specimen used in the above tests fails to meet the specified requirements, disposition of the castings may be based on the results of testing three additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the castings represented and no additional testing shall be permitted. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY:

- 5.1 Identification: Castings shall be identified in accordance with AMS 2804.