



# AEROSPACE MATERIAL SPECIFICATION

**AMS5532™****REV. J**

Issued 1947-09  
Reaffirmed 2012-07  
Revised 2022-01

Superseding AMS5532H

Iron Alloy, Corrosion and Heat-Resistant, Sheet, Strip, and Plate  
30Fe - 21Cr - 20Ni - 20Co - 3.0Mo - 2.5W - 1.0Cb(Nb) - 0.15N  
Solution Heat Treated  
(Composition similar to UNS R30155)

## RATIONALE

AMS5532J is the result of a Five-Year Review and update of the specification. The revision updates exception requirements (3.6, 8.4, 8.6), adds strain rate for tensile tests (3.3.1), and revises reports (4.4).

### 1. SCOPE

#### 1.1 Form

This specification covers a corrosion and heat-resistant iron alloy in the form of sheet, strip, and plate.

#### 1.2 Application

These products have been used typically for parts requiring high strength up to 1500 °F (816 °C) and oxidation resistance up to 1800 °F (982 °C), but usage is not limited to such applications.

### 2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

#### 2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), [www.sae.org](http://www.sae.org).

AMS2242 Tolerances Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate

AMS2248 Chemical Check Analysis Limits Corrosion and Heat-Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2022 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: [CustomerService@sae.org](mailto:CustomerService@sae.org)  
<http://www.sae.org>

SAE WEB ADDRESS:

For more information on this standard, visit  
<https://www.sae.org/standards/content/AMS5532J>

AMS2371	Quality Assurance Sampling and Testing Corrosion and Heat-Resistant Steels and Alloys Wrought Products and Forging Stock
AMS2807	Identification Carbon and Low-Alloy Steels, Corrosion and Heat-Resistant Steels and Alloys Sheet, Strip, Plate, and Aircraft Tubing
AS4194	Sheet and Strip Surface Finish Nomenclature
AS7766	Terminology Used in Aerospace Metals Specifications

## 2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, [www.astm.org](http://www.astm.org).

ASTM A480/A480M	Flat-Rolled Stainless and Heat-Resisting Steel Plate, Sheet, and Strip
ASTM E8/E8M	Tension Testing of Metallic Materials
ASTM E139	Conducting Creep, Creep-Rupture, and Stress-Rupture Tests of Metallic Materials
ASTM E290	Bend Testing of Material for Ductility
ASTM E354	Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

## 3. TECHNICAL REQUIREMENTS

### 3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined in accordance with ASTM E354 or by other analytical methods acceptable to purchaser.

**Table 1 - Composition**

Element	Min	Max
Carbon	0.08	0.16
Manganese	1.00	2.00
Silicon	--	1.00
Phosphorus	--	0.040
Sulfur	--	0.030
Chromium	20.00	22.50
Nickel	19.00	21.00
Cobalt	18.50	21.00
Molybdenum	2.50	3.50
Tungsten	2.00	3.00
Columbium (Niobium)	0.75	1.25
Nitrogen	0.10	0.20
Tantalum	--	0.05
Copper	--	0.50
Iron	remainder	

#### 3.1.1 Check Analysis

Composition variations shall meet the applicable requirements of AMS2248.

### 3.2 Condition

The product shall be supplied in the following condition:

### 3.2.1 Sheet and Strip

Hot or cold rolled, solution heat treated, and, unless solution heat treatment is performed in an atmosphere yielding a bright finish, descaled, having a surface appearance as described in ASTM A480/A480M and AS4194 and 3.2.1.1 or 3.2.1.2 as applicable.

#### 3.2.1.1 Sheet

No. 2D finish.

#### 3.2.1.2 Strip

No. 1 strip finish.

### 3.2.2 Plate

Hot rolled, solution heat treated, and descaled.

## 3.3 Properties

The product shall conform to the following requirements:

### 3.3.1 Tensile Properties

Shall be as shown in Table 2, determined in accordance with ASTM E8/E8M.

**Table 2 - Room temperature tensile properties**

Property	Value
Tensile Strength	100 to 140 ksi (689 to 965 MPa)
Elongation in 2 inches (50mm) or 4D, min	40%

3.3.1.1 Unless otherwise specified, the strain rate shall be set at 0.005 in/in/min (0.005 mm/mm/min) and maintained within a tolerance of  $\pm 0.002$  in/in/min ( $\pm 0.002$  mm/mm/min) through 0.2% offset yield strain. The strain rate after yield may be increased to any value up to 0.5 in/in/min (or 0.5 mm/mm/min) or equivalent crosshead speed as a function of gage length.

### 3.3.2 Bending

Product 0.1874 inch (4.760 mm) and under in nominal thickness shall be tested in accordance with ASTM E290 using a sample prepared nominally 0.75 inch (19.0 mm) in width with its axis of bending parallel to the direction of rolling and shall withstand, without cracking, when bending at room temperature through an angle of 180 degrees around a diameter equal to the bend factor shown in Table 3 times the nominal thickness of the product. In case of dispute, the results of tests using the guided bend test of ASTM E290 shall govern.

**Table 3 - Bending parameters**

Nominal Thickness Inches	Nominal Thickness Millimeters	Bend Factor
Up to 0.050, incl	Up to 1.27, incl	1
Over 0.050 to 0.125, incl	Over 1.27 to 3.18, incl	2
Over 0.125 to 0.1874, incl	Over 3.18 to 4.760, incl	3

### 3.3.3 Stress-Rupture Properties at 1500 °F (816 °C)

A tensile specimen, maintained at 1500 °F  $\pm$  3 °F (816 °C  $\pm$  2 °C) while a load sufficient to produce an initial axial stress of 18.0 ksi (124 MPa) or higher is applied continuously, shall not rupture in less than 24 hours. The test shall be continued to rupture without change of load. Elongation after rupture, measured at room temperature, shall be not less than 10% in 2 inches (50.8 mm) or 4D. Tests shall be conducted in accordance with ASTM E139.

3.3.3.1 The test of 3.3.3 may be conducted using incremental loading. In such case, the load required to produce an initial axial stress of 18.0 ksi (124 MPa) or higher shall be maintained to rupture or for 24 hours, whichever occurs first. After the 24 hours and at intervals of 8 hours minimum, thereafter, the stress shall be increased in increments of 2.0 ksi (14 MPa). Time to rupture and elongation requirements shall be as specified in 3.3.3.

### 3.4 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

### 3.5 Tolerances

Shall conform to all applicable requirements of AMS2242.

### 3.6 Exceptions

Any exceptions shall be authorized by the purchaser and reported as in 4.4.1.

## 4. QUALITY ASSURANCE PROVISIONS

### 4.1 Responsibility for Inspection

The producer of the product shall supply all samples for producer's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

### 4.2 Classification of Tests

All technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.

### 4.3 Sampling and Testing

Shall be in accordance with AMS2371.

### 4.4 Reports

The producer of the product shall furnish with each shipment a report showing the producer's name and the country where the metal was melted (e.g., final melt in the case of metal processed by multiple melting operations) and stating the product conforms to the composition, and tolerances, , and showing the numerical results of tests on each inspection lot to determine conformance to the other acceptance test requirements. This report shall include the purchase order number, inspection lot numbers, AMS5532J, size, and quantity. The report shall also identify the producer, the product form, and the size of the mill product.

4.4.1 When material produced to this specification has exceptions taken to the technical requirements listed in Section 3 (see 5.1.1), the report shall contain a statement "This material is certified as AMS5532J(EXC) because of the following exceptions:" and the specific exceptions shall be listed.

### 4.5 Resampling and Retesting

Shall be in accordance with AMS2371.