

AEROSPACE MATERIAL SPECIFICATION



AMS 5605D

Issued NOV 1971
Revised OCT 2000

Superseding AMS 5605C

Nickel Alloy, Corrosion and Heat Resistant, Sheet, Strip, and Plate

41.5Ni - 16Cr - 37Fe - 2.9Cb - 1.8Ti

Consumable Electrode or Vacuum Induction Melted

1800 °F (982 °C) Solution Heat Treated

UNS N09706

1. SCOPE:

1.1 Form:

This specification covers a corrosion and heat resistant nickel alloy in the form of sheet, strip, and plate 1.00 inch (25.4 mm) and under in nominal thickness.

1.2 Application:

These products have been used typically for parts requiring good machinability and high strength at room and cryogenic temperatures and for short-time use up to 1000 °F (538 °C), particularly for those parts which are formed or welded and then heat treated to develop required properties, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2262	Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Sheet, Strip, and Plate
MAM 2262	Tolerances, Metric, Nickel, Nickel Alloy, and Cobalt Alloy Sheet, Strip, and Plate
AMS 2269	Chemical Check Analysis Limits, Nickel, Nickel Alloys and Cobalt Alloys
AMS 2371	Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2000 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:

TO PLACE A DOCUMENT ORDER:

SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

2.1 (Continued):

AMS 2807 Identification, Carbon and Low-Alloy Steels, Corrosion and Heat Resistant Steels and Alloys, Sheet, Strip, Plate, and Aircraft Tubing

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM E 8 Tension Testing of Metallic Materials
 ASTM E 8M Tension Testing of Metallic Materials (Metric)
 ASTM E 18 Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials
 ASTM E 112 Determining the Average Grain Size
 ASTM E 290 Semi-Guided Bend Test for Ductility of Metallic Materials
 ASTM E 354 Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys
 ASTM E 384 Microhardness of Materials

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 354, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	--	0.06
Manganese	--	0.35
Silicon	--	0.35
Phosphorus	--	0.020
Sulfur	--	0.015
Chromium	14.50	17.50
Nickel	39.00	44.00
Columbium	2.50	3.30
Tantalum	--	0.05
Titanium	1.50	2.00
Aluminum	--	0.40
Boron	--	0.006
Copper	--	0.30
Iron	remainder	

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2269.

3.2 Melting Practice:

Alloy shall be produced by multiple melting using consumable electrode practice in the remelt cycle or shall be induction melted under vacuum. If consumable electrode remelting is not performed in vacuum, electrodes which have been produced by vacuum induction melting shall be used for remelting.

3.3 Condition:

The product shall be supplied in the following condition:

3.3.1 Sheet and Strip: Cold rolled, solution heat treated free from continuous carbide network and, unless solution heat treatment is performed in an atmosphere yielding a bright finish, descaled having a surface appearance comparable to the following commercial corrosion-resistant steel finishes as applicable (See 8.2).

3.3.1.1 Sheet: No. 2D finish.

3.3.1.2 Strip: No. 1 Strip finish.

3.3.2 Plate: Hot rolled, solution heat treated, and descaled.

3.4 Heat Treatment:

No specific solution heat treatment is specified but it is recommended that the product be solution heat treated by heating in a suitable protective atmosphere to a temperature within the range 1750 to 1850 °F (954 to 1010 °C), holding at the selected temperature within ± 25 °F (± 14 °C) for a time commensurate with section thickness but not less than five minutes, and cooling at a rate equivalent to an air cool or faster.

3.5 Properties:

The product shall conform to the following requirements:

3.5.1 As Solution Heat Treated:

3.5.1.1 Tensile Properties: Shall be as shown in Table 2, determined in accordance with ASTM E 8 or ASTM E 8M.

TABLE 2A - Tensile Properties, Inch/Pound Units

Nominal Thickness Inch	Tensile Strength ksi, max	Yield Strength at 0.2% Offset ksi, max	Elongation in 2 Inches or 4D %, min
Up to 0.1875, excl	130	80.0	30
0.1875 and over	140	90.0	30

TABLE 2B - Tensile Properties, SI Units

Nominal Thickness Millimeters	Tensile Strength MPa, max	Yield Strength at 0.2% Offset MPa, max	Elongation in 50.8 mm or 4D %, min
Up to 4.762, excl	896	552	30
4.762 and over	965	621	30

- 3.5.1.2 Hardness: Shall be not higher than shown in Table 3, or equivalent (See 8.3), determined in accordance with ASTM E 18; for thin gages, where superficial hardness testing is impractical, microhardness testing in accordance with ASTM E 384 may be used. Product shall not be rejected on the basis of hardness if the tensile properties of 3.5.1.1 are acceptable, determined on specimens taken from the same sample as that with nonconforming hardness or from another sample with similar nonconforming hardness.

TABLE 3 - Maximum Hardness

Nominal Thickness Inch	Nominal Thickness Millimeters	Hardness
Up to 0.1875, excl	Up to 4.762, excl	102 HRB
0.1875 and over	4.762 and over	25 HRC

- 3.5.1.3 Bending: Product under 0.1875 inch (4.762 mm) in nominal thickness shall withstand, without cracking, bending in accordance with ASTM E 290 through an angle of 180 degrees around a diameter equal to the bend factor shown in Table 4 times the nominal thickness of the product with axis of bend parallel to the direction of rolling.

TABLE 4 - Bending Parameters

Nominal Thickness Inch	Nominal Thickness Millimeters	Bend Factor
Up to 0.050, incl	Up to 1.27, incl	1
Over 0.050 to 0.1875, excl	Over 1.27 to 4.762, excl	2

3.5.1.4 Average Grain Size: Shall be as shown in Table 5, determined in accordance with ASTM E 112:

TABLE 5 - Average Grain Size

Nominal Thickness Inch	Nominal Thickness Millimeters	ASTM Grain Size No.
Up to 0.1875, excl	Up to 4.762, excl	5 or finer
0.1875 and over	4.762 and over	4 or finer

3.5.2 After Precipitation Heat Treatment: The product shall have the following properties after being precipitation heat treated by heating to 1350 °F ± 15 (732 °C ± 8), holding at heat for 8 hours ± 0.25, cooling at a rate of 100 F (56 C) degrees per hour to 1150 °F ± 15 (621 °C ± 8), holding at 1150 °F ± 15 (621 °C ± 8) for 8 hours ± 0.25, and cooling in air. Instead of the 100 F (56 C) degrees per hour cooling rate to 1150 °F ± 15 (621 °C ± 8), the furnace cooling may be at any rate provided the time at 1150 °F ± 15 (621 °C ± 8) is adjusted to give a total precipitation heat treatment time of not less than 18 hours.

3.5.2.1 Tensile Properties: Shall be as shown in Table 6, determined in accordance with ASTM E 8 or ASTM E 8M.

TABLE 6A - Minimum Tensile Properties, Inch/Pound Units

Nominal Thickness Inch	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inches or 4D %
Up to 0.1875, excl	175	145	12
0.1875 and over	170	145	12

TABLE 6B - Minimum Tensile Properties, SI Units

Nominal Thickness Millimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm or 4D %
Up to 4.762, excl	1207	1000	12
4.762 and over	1172	965	12

3.5.2.2 Hardness: Shall be not lower than 34 HRC, or equivalent (See 8.3), determined in accordance with ASTM E 18; for thin gages, where superficial hardness testing is impractical, microhardness testing in accordance with ASTM E 384 may be used. Product shall not be rejected on the basis of hardness if the tensile properties of 3.5.2.1 are acceptable, determined on specimens taken from the same sample as that with nonconforming hardness or from another sample with similar nonconforming hardness.