

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®
INTERNATIONAL

400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

SAE

AMS 5800D

Issued 15 JAN 1962
Revised 1 JAN 1992
Superseding AMS 5800C

ALLOY, CORROSION AND HEAT RESISTANT, WELDING WIRE
54Ni - 19Cr - 11Co - 10Mo - 3.2Ti - 1.5Al - 0.006B

UNS N07041

1. SCOPE:

1.1 Form:

This specification covers a corrosion and heat resistant nickel alloy in the form of welding wire.

1.2 Application:

Primarily for use as filler metal for gas-tungsten-arc or gas-metal-arc welding of parts fabricated from alloys of similar composition.

1.3 Classification:

Welding wire covered by this specification is classified as follows:

Type I - Alloy multiple melted using vacuum induction followed by vacuum consumable electrode practice.

Type II - Alloy multiple melted using vacuum induction followed by electroslag practice in the final melting.

1.3.1 Unless a specific type is ordered, either type may be supplied.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

AMS 5800D

SAE

AMS 5800D

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2269 Chemical Check Analysis Limits, Wrought Nickel Alloys and Cobalt Alloys

AMS 2371 Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock

AMS 2813 Packaging of Welding Wire, Standard Method

AMS 2814 Packaging of Welding Wire, Premium Quality

AMS 2816 Identification, Welding Wire, Color Code System

ARP1876 Weldability Test for Weld Filler Metal Wire

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM E 354 Chemical Analysis of High-Temperature, Electrical, Magnetic, and Other Similar Iron, Nickel, and Cobalt Alloys

3. TECHNICAL REQUIREMENTS:

3.1 Composition:
(R)

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 354, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	--	0.12
Manganese	--	0.10
Silicon	--	0.50
Sulfur	--	0.015
Chromium	18.00	20.00
Cobalt	10.00	12.00
Molybdenum	9.00	10.50
Titanium	3.00	3.30
Aluminum	1.40	1.60
Boron	0.003	0.010
Iron	--	5.00
Nickel	remainder	

AMS 5800D

SAE

AMS 5800D

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2269.

3.2 Melting Practice:

Alloy shall be produced by multiple melting using vacuum induction followed by either vacuum consumable electrode practice or electroslog practice in the final melting.

3.3 Condition:

(R)

Cold worked, bright finished, in a temper and with a surface finish which will provide proper feeding of the wire in machine welding equipment.

3.3.1 Wire shall be furnished on disposable spools for machine welding or in cut lengths for manual welding, as ordered.

3.3.2 In-process annealing between cold rolling or drawing operations shall be performed in a suitable protective atmosphere.

3.3.3 Drawing compounds, oxides, dirt, oil, and other surface contamination shall be removed by cleaning processes which will neither result in pitting nor cause gas absorption by the wire or deposition of substances harmful to welding operations.

3.4 Properties:

Wire shall conform to the following requirements:

3.4.1 Weldability: Melted wire shall flow smoothly and evenly during welding and shall produce acceptable welds. ARP1876 may be used to resolve disputes.

3.4.2 Spooled Wire: Shall conform to 3.4.2.1 and 3.4.2.2.

3.4.2.1 Cast: Wire, wound on standard 12-inch (305-mm) diameter spools, shall have imparted to it a curvature such that a specimen sufficient in length, 4 - 14 feet (1.2 - 4.3 m), to form one loop, when cut from the spool and laid on a flat surface, shall form a circle 15 - 50 inches (381 - 1270 mm) in diameter.

3.4.2.2 Helix: The specimen on which cast was determined, when laid on a flat surface and measured between adjacent turns, shall show a vertical separation not greater than 1 inch (25 mm).

3.5 Quality:

Wire, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.



AMS 5800D

SAE

AMS 5800D

3.6 Sizes and Tolerances:

Wire shall be supplied in the standard sizes and to the tolerances shown in Table 2 and 3.6.2.

3.6.1 Diameter:

TABLE 2A - Diameter Tolerances , Inch/Pound Units

Form	Nominal Diameter Inch	Tolerance Inch plus	Tolerance Inch minus
Cut Lengths	0.030, 0.045, 0.062, 0.078	0.002	0.002
Cut Lengths	0.094, 0.125, 0.156, 0.188	0.003	0.003
Spools	0.007, 0.010, 0.015, 0.020	0.0005	0.0005
Spools	0.030, 0.035, 0.045	0.001	0.002
Spools	0.062, 0.078, 0.094	0.002	0.002

TABLE 2B - Diameter Tolerances, SI Units

Form	Nominal Diameter Millimeters	Tolerance Millimeter plus	Tolerance Millimeter minus
Cut Lengths	0.76, 1.14, 1.57, 1.98	0.05	0.05
Cut Lengths	2.39, 3.18, 3.96, 4.78	0.08	0.08
Spools	0.18, 0.25, 0.38, 0.51	0.013	0.013
Spools	0.76, 0.89, 1.14	0.025	0.05
Spools	1.57, 1.98, 2.39	0.05	0.05

3.6.2 Length: Cut lengths shall be furnished in 18, 27, or 36 inch (457, 686, or 914 mm) lengths, as ordered, and shall not vary more than +0, -0.5 inch (-13 mm) from the length ordered.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:
(R)

The vendor of wire shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to the requirements of this specification.