

**AEROSPACE  
MATERIAL  
SPECIFICATION****AMS 6304J**

Issued	AUG 1955
Reaffirmed	SEP 2000
Revised	FEB 2004
Superseding AMS 6304H	

Low-Alloy Steel, Heat-Resistant, Bars, forgings, and Tubing  
0.95Cr - 0.55Mo - 0.30V (0.40 - 0.50C)  
(Composition similar to UNS K14675)

**1. SCOPE:****1.1 Form:**

1.1.1 This specification covers an aircraft-quality, low-alloy, heat-resistant steel in the form of bars, forgings, mechanical tubing, and forging stock.

**1.2 Application:**

These products have been used typically for parts, such as shafts and fasteners, in service up to 1000 °F (540 °C), but usage is not limited to such applications.

**2. APPLICABLE DOCUMENTS:**

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

**2.1 SAE Publications:**

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001 or [www.sae.org](http://www.sae.org).

AMS 2251	Tolerances, Low-Alloy Steel Bars
AMS 2253	Tolerances, Carbon and Alloy Steel Tubing
AMS 2259	Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
AMS 2301	Steel Cleanliness, Aircraft-Quality Magnetic Particle Inspection Procedure
AMS 2370	Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Wrought Products and Forging Stock
AMS 2372	Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Forgings
AMS 2806	Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat-Resistant Steels and Alloys

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2004 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:** Tel: 877-606-7323 (inside USA and Canada)  
Tel: 724-776-4970 (outside USA)

Fax: 724-776-0790  
Email: [custsvc@sae.org](mailto:custsvc@sae.org)  
<http://www.sae.org>

**SAE WEB ADDRESS:**

## 2.1 (Continued):

AMS 2808 Identification, forgings

AS1182 Standard machining allowance, aircraft-quality and premium aircraft-quality steel bars and mechanical tubing

## 2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959 or [www.astm.org](http://www.astm.org).

ASTM A 370 Mechanical Testing of Steel Products

ASTM E 112 Determining Average Grain Size

ASTM E 350 Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

ASTM E 381 Macroetch Testing Steel Bars, Billets, Blooms, and Forgings

ASTM E 384 Microindentation Hardness of Materials

## 3. TECHNICAL REQUIREMENTS:

## 3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 350, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	0.40	0.50
Manganese	0.40	0.70
Silicon	0.15	0.35
Phosphorus	--	0.025
Sulfur	--	0.025
Chromium	0.80	1.10
Molybdenum	0.45	0.65
Vanadium	0.25	0.35
Nickel	--	0.25
Copper	--	0.35

## 3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

## 3.2 Condition:

The product shall be supplied in the following condition; hardness and tensile strength shall be determined in accordance with ASTM A 370:

## 3.2.1 Bars:

- 3.2.1.1 Bars 0.500 Inch (12.70 mm) and Under in Nominal Diameter or Least Distance Between Parallel Sides: Cold finished having tensile strength not higher than 125 ksi (862 MPa) or equivalent hardness (See 8.2).
- 3.2.1.2 Bars Over 0.500 Inch in Nominal Diameter or Least Distance Between Parallel Sides: Hot finished and annealed unless otherwise ordered, having hardness not higher than 229 HB, or equivalent (See 8.3). Bars ordered cold finished may have hardness as high as 248 HB, or equivalent (See 8.3).
- 3.2.2 forgings: Annealed having hardness not higher than 248 HB, or equivalent (See 8.3).
- 3.2.3 Mechanical Tubing: Cold finished unless otherwise ordered, having hardness not higher than 25 HRC, or equivalent (See 8.3). Tubing ordered hot finished and annealed shall have hardness not higher than 99 HRB, or equivalent (See 8.3).
- 3.2.4 Forging Stock: As ordered by the forging manufacturer.

## 3.3 Properties:

The product shall conform to the following requirements; hardness testing shall be performed in accordance with ASTM A 370:

- 3.3.1 Macrostructure: Visual examination of transverse full cross-sections from bars, billets, tube rounds, and forging stock, etched in hot hydrochloric acid in accordance with ASTM E 381, shall show no pipe or cracks. Porosity, segregation, inclusions, and other imperfections shall be no worse than the macrographs of ASTM E 381 shown in Table 2.

TABLE 2 - Macrostructure Limits

Cross-Section Area		Macrographs
Square Inches		
Up to	36, incl	S2 - R1 - C2
Over	36 to 100, incl	S2 - R2 - C3

- 3.3.2 Average Grain Size: Shall be ASTM No. 5 or finer, determined in accordance with ASTM E 112.

## 3.3.3 Decarburization:

- 3.3.3.1 Bars and tubing ordered ground, turned, or polished shall be free from decarburization on the ground, turned, or polished surfaces.
- 3.3.3.2 Allowable decarburization of bars, billets, tube rounds, and tubing ordered for redrawing or forging or to specified microstructural requirements shall be as agreed upon by purchaser and vendor.

3.3.3.3 Decarburization of bars to which 3.3.3.1 or 3.3.3.2 is not applicable shall be not greater than shown in Table 3.

TABLE 3A - Maximum Depths of Decarburization, Inch/Pound Units

Nominal Diameter or Distance Between Parallel Sides Inches	Total Depth of Decarburization Inch
Up to 0.375, incl	0.015
Over 0.375 to 0.500, incl	0.017
Over 0.500 to 0.625, incl	0.019
Over 0.625 to 1.000, incl	0.022
Over 1.000 to 1.500, incl	0.025
Over 1.500 to 2.000, incl	0.030
Over 2.000 to 2.500, incl	0.035
Over 2.500 to 3.000, incl	0.040
Over 3.000 to 4.000, incl	0.045

TABLE 3B - Maximum Depth of Decarburization, SI Units

Nominal Diameter or Distance Between Parallel Sides Millimeters	Total Depth of Decarburization Millimeter
Up to 9.52, incl	0.38
Over 9.52 to 12.70, incl	0.43
Over 12.70 to 15.88, incl	0.48
Over 15.88 to 25.40, incl	0.56
Over 25.40 to 38.10, incl	0.64
Over 38.10 to 50.80, incl	0.76
Over 50.80 to 63.50, incl	0.89
Over 63.50 to 76.20, incl	1.02
Over 76.20 to 101.60, incl	1.14

3.3.3.4 Decarburization of tubing to which 3.3.3.1 or 3.3.3.2 is not applicable shall be not greater than shown in Table 4.

TABLE 4A - Maximum Depths of Decarburization, Inch/Pound Units

Nominal Wall Thickness Inches	Total Depth of Decarburization Inch ID	Total Depth of Decarburization Inch OD
		OD
Up to 0.109, incl	0.008	0.020
Over 0.109 to 0.203, incl	0.010	0.025
Over 0.203 to 0.400, incl	0.012	0.030
Over 0.400 to 0.600, incl	0.015	0.035
Over 0.600 to 1.000, incl	0.017	0.040
Over 1.000	0.020	0.045

TABLE 4B - Maximum Depth of Decarburization, SI Units

Nominal Wall Thickness Millimeters	Total Depth of Decarburization Millimeters	Total Depth of Decarburization Millimeters	
		ID	OD
Up to 2.77, incl	0.20	0.50	
Over 2.77 to 5.16, incl	0.25	0.64	
Over 5.16 to 10.16, incl	0.30	0.76	
Over 10.16 to 15.24, incl	0.38	0.89	
Over 15.24 to 25.40, incl	0.43	1.02	
Over 25.40	0.51	1.14	

3.3.3.5 Decarburization shall be measured by the metallographic method, by the HR30N scale hardness testing method, or by a traverse method using microhardness testing in accordance with ASTM E 384. The hardness method(s) shall be conducted on a hardened but untempered specimen protected during heat treatment to prevent changes in surface carbon content. Depth of decarburization, when measured by a hardness method, is defined as the perpendicular distance from the surface to the depth under that surface below which there is no further increase in hardness. Such measurements shall be far enough away from any adjacent surface to be uninfluenced by any decarburization on the adjacent surface. In case of dispute, the depth of decarburization determined using the microhardness traverse method shall govern.

3.3.3.5.1 When determining the depth of decarburization, it is permissible to disregard local areas provided the decarburization of such areas does not exceed the above limits by more than 0.005 inch (0.13 mm) and the width is 0.065 inch (1.65 mm) or less.

3.3.4 Response to Heat Treatment: Specimens as in 4.3.3 shall have hardness at the center of the specimen not lower than 331 HB, or equivalent (See 8.3), for cross-sections 2 inches (50.8 mm) and under and not lower than 302 HB, or equivalent (See 8.3), for larger cross-sections after being heated to  $1750^{\circ}\text{F} \pm 25$  ( $954^{\circ}\text{C} \pm 14$ ), held at heat for 60 to 90 minutes, cooled at a rate equivalent to still air cooling, reheated to  $1100^{\circ}\text{F} \pm 15$  ( $593^{\circ}\text{C} \pm 8$ ), held at heat for 6 hours  $\pm 0.25$ , and cooled in air.

### 3.4 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.4.1 Steel shall be aircraft quality conforming to AMS 2301.

3.4.2 Bars and mechanical tubing ordered hot rolled or cold drawn or ground, turned, or polished shall, after removal of the standard machining allowance in accordance with AS1182, be free from seams, laps, tears, and cracks open to the ground, turned, or polished surface.

3.4.3 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of reentrant grain flow.

3.5 Tolerances:

Shall be as follows:

3.5.1 Bars: Shall conform to all applicable requirements of AMS 2251.

3.5.2 Mechanical Tubing: Shall conform to all applicable requirements of AMS 2253.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests:

All technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling and Testing:

Shall be as follows:

4.3.1 Bars, Mechanical Tubing, and Forging Stock: In accordance with AMS 2370.

4.3.2 Forgings: In accordance with AMS 2372.

4.3.3 Specimens for response to heat treatment (3.3.4) shall be not shorter than twice the nominal diameter or distance between parallel sides or 6 inches (152 mm), whichever is less, and shall have the full cross-section of the product from which they were cut except that sections over 2 to 4 inches (over 51 to 102 mm), inclusive, in nominal diameter or least distance between parallel sides shall be reduced to 2.00 inches  $\pm$  0.01 (51 mm  $\pm$  0.03) and sections over 4 inches (102 mm) shall be reduced to 4.00 inches  $\pm$  0.01 (101.6 mm  $\pm$  0.03)

4.4 Reports:

The vendor of the product shall furnish with each shipment a report showing the results of tests for composition, macrostructure, and frequency-severity cleanliness rating of each heat, and for average grain size and response to heat treatment of each lot, and stating that the product conforms to the other technical requirements.. This report shall include the purchase order number, heat and lot numbers, AMS 6304J, size, and quantity. If forgings are supplied, the size and melt source of stock used to make the forgings shall also be included.