

National Aerospace and Defense Contractors Accreditation Program
Requirements for Electrochemical Machining (ECM)

RATIONALE

AS7116/1A is being cancelled and superseded by PRI AC7116/1. The requirements in the document have not changed.

CANCELLATION NOTICE

This document has been declared "CANCELLED" as of July 2008 and has been superseded by AC7116/1. By this action, this document will remain listed in the Numerical Section of the Aerospace Standards Index noting that it is superseded by AC7116/1.

SAENORM.COM : Click to view the full PDF of as7116-1a

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2008 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

1. SCOPE:

This Aerospace Standard (AS) is to be used to supplement AS7116. In addition to the requirements contained in AS7116, the requirements contained herein shall apply to suppliers seeking NADCAP accreditation for electrochemical machining (ECM).

2. REFERENCES:

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15086-0001.

- AS7101/4 National Aerospace and Defense Contractors Accreditation Program (NADCAP) – Requirements for Materials Testing Laboratories – Metallography and Microhardness
- AS7108 National Aerospace and Defense Contractors Accreditation Program (NADCAP) – Audit Criteria for Chemical Processing
- AS7116 National Aerospace and Defense Contractors Accreditation Program (NADCAP) – Requirements for Nonconventional Machining.

2.2 PRI Documents:

Available from Performance Review Institute, 161 Thornhill Road, Warrendale, PA 15086-7527.

- AC7116/1 National Aerospace and Defense Contractors Accreditation Program (NADCAP) – Audit Criteria for Electrochemical Machining (ECM)

SAENORM.COM : Click to view the full PDF of as7116/1A

2.3 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428

ASTM E3 Methods of Preparation of Metallographic Specimens

2.4 Applicable customer specifications shall be available at the facility.

3. EQUIPMENT:

3.1 Calibration of ECM Meters and Gages:

An ECM calibration plan shall exist and include the following items, when they are present for the ECM process:

- a. Electrolyte pressure gages and/or flowmeters
- b. Volt meters
- c. Ammeters
- d. Specific gravity, temperature, or conductivity tools used to determine electrolyte concentration

3.2 Maintenance

An ECM machine preventative maintenance plan shall exist and include the following, where applicable:

- a. Cathode holders
- b. Shuttles
- c. Masks
- d. Pressure boxes
- e. Slaves
- f. Ram extensions
- g. Electrical cables and connectors
- h. Power supply
- i. Motors
- j. Electrolyte filtration
- k. Machine ways
- l. Hydraulic system
- m. Electrical cabinet filters
- n. Arc detection/suppression circuitry

3.2.1 There shall be a documented schedule for preventative maintenance.

3.2.2 There shall be a preventative maintenance completion document.

4. WORK INSTRUCTION REQUIREMENTS:

4.1 Tooling and Support Material:

4.1.1 Fixtures/Tooling:

4.1.1.1 The tool fixture shall be listed by tool number and/or description when no tool number is available.

4.1.1.2 Any additional tools and production aids shall be listed by tool number and/or description when no tool number is available.

4.1.2 Support Tooling:

The following support tools shall be listed by tool number, where applicable:

- a. Cathode holders
- b. Shuttles
- c. Masks
- d. Pressure boxes
- e. Slaves
- f. Ram extensions
- g. Locators

4.1.3 Cathodes:

4.1.3.1 The cathode shall be listed by drawing number or by the supplier's control number.

4.1.3.2 There shall be a cathode revision control plan that includes the following items:

- a. Procedure to ensure that the correct cathode revision is in use
- b. Software quality control of programs used to manufacture cathodes
- c. Procedures used to manually dress, polish or modify cathode geometry

4.2 Restart Procedure:

4.2.1 The ECM machine restart procedure shall be described.

4.3 Non-Machined Surfaces:

4.3.1 The method for protecting non-machined surfaces shall be described.

4.3.2 The method for protecting non-machined surfaces shall be approved, if required by the customer.

4.4 Electrical Bussing:

4.4.1 Procedures for electrical buss contact connection and connection verification shall be described.

4.5 Workpiece Loading:

4.5.1 The part loading and loading verification procedure shall be described.

4.6 Work Instruction Approval:

4.6.1 Work instructions shall be approved in accordance with customer requirements.

4.7 ECM Machine Electrolyte Control:

4.7.1 The workstation instructions shall describe the following, where applicable:

- a. Electrolyte inlet and/or outlet pressure ranges
- b. Flow rate control

4.8 ECM Parameter Requirements:

4.8.1 The ECM workstation instructions shall list values or ranges for the following ECM parameters, where applicable:

- a. Gap machining voltage or maximum amperage
- b. Feedrate
- c. Machine control program name or schedule ID or number

4.8.2 Where ECM machines have controls for parameters that are not listed in Paragraph 4.8.1, the workstation instructions shall list values or limits for the additional parameters.

5. QUALITY PLANS:

5.1 Procedure:

5.1.1 There shall be a quality plan for each ECM operation and part processed that includes the following, as applicable:

- a. Dimensions to be checked
- b. Method of control (i.e., fixture, cathode, machine program)
- c. Method of inspection
- d. Frequency of inspection
- e. Visual examination to detect pitting
- f. Visual comparison of surface finish
- g. Metallurgical checks and frequency
- h. Part cleaning procedure prior to and after processing

5.2 Quality Plan Approval:

5.2.1 The quality plan shall be approved in accordance with customer requirements.

5.2.2 The customer shall approve the use of any sampling plans.

5.3 Gages:

- 5.3.1 For those dimensions measured at the ECM operation, the quality plan shall list the gage by a drawing, gage number, or standard gage description.

5.4 ECM Surface Integrity:

- 5.4.1 The quality plan shall have a section that addresses ECM sparkout events or damage that occurs during ECM that includes the following:
- a. Purchaser notification procedure
 - b. Documentation that identifies part number and/or serial number, ECM operation number, workpiece sparkout location, and sparkout cause and corrective action determination

6. ELECTROLYTE CONTROL:

- 6.1 There shall be an electrolyte control plan that covers the following items, where applicable:
- a. Describe the electrolyte used
 - b. Define electrolyte concentration, conductivity, or specific gravity limits
 - c. Electrolyte temperature operating range
 - d. Electrolyte composition check interval
 - e. Maximum allowable buildup for metallic elements
 - f. Schedule for checking concentration and dissolution products
 - g. Solution found to be out of process limits
- 6.2 If the electrolyte is out of limits, there shall be a procedure for evaluating any metallurgical damage to the workpiece.
- 6.3 There shall be a procedure for notifying the customer that workpieces were processed with an electrolyte solution that was out of customer approved limits.
- 6.4 If electrolyte concentration is calculated by measuring electrolyte conductivity or specific gravity at a known temperature, the person responsible for maintaining the electrolyte shall have tables or conversion information to calculate concentration.

7. ANCILLARY PROCESSES:

7.1 Part Cleaning:

- 7.1.1 Part cleaning shall be performed on processed parts either in-house or by an outside source.

7.1.1.1 If conducted in-house, one of the following shall apply:

- a. NADCAP accredited to SAE AS7108, proceed to Paragraph 8
- b. Not accredited to SAE AS7108, only de-ionized or tap water used, proceed to Paragraph 8
- c. Not accredited to SAE AS7108, cleaning solutions used, Paragraphs 7.1.2 through 7.1.10 shall be addressed

- 7.1.1.2 If conducted by an outside source, proceed to Paragraph 8.
- 7.1.2 Workstation instructions shall be available at the cleaning workstation.
- 7.1.3 If required, workstation instructions shall be approved in accordance with customer requirements.
- 7.1.4 If required, cleaning solutions shall be approved by the purchaser.
- 7.1.5 The following controls shall be calibrated, if applicable:
 - a. Temperature gage
 - b. Timer
- 7.1.6 The cleaning tank agitator shall be functioning, if applicable.
- 7.1.7 The maximum tank time shall be posted or listed in the workstation instructions, if applicable.
- 7.1.8 The rinse tank cleanliness and check interval shall be defined, if applicable.
- 7.1.9 There shall be a solution concentration testing and makeup procedure, if applicable.
- 7.1.10 The cleaning operator shall receive required supplier training.

8. LABORATORY ANALYSIS

8.1 Inspection:

- 8.1.1 There shall be a laboratory analysis that shows conformance to applicable drawing notes and/or related specifications.
- 8.1.2 The samples used to demonstrate conformance shall meet the following:
 - a. Machined using the same ECM process parameters used in production
 - b. Same material and heat treat condition as production parts, if applicable

8.2 Periodic Metallurgical Evaluation:

- 8.2.1 Periodic testing shall be performed to verify compliance to the customer's metallurgical requirements, if required.
- 8.2.2 Metallographic testing on processed parts shall be conducted by an approved source, either in-house or by an outside source, if required by the customer.
 - 8.2.2.1 If conducted in-house, one of the following shall apply:
 - a. NADCAP accredited to SAE AS7101/4, proceed to Paragraph 9
 - b. Initially approved by NADCAP subscribing customer, Paragraphs 8.2.3 through 8.2.9 shall be addressed