


SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

REV. A	FEDERAL SUPPLY CLASS 6145	
	RATIONALE THIS DOCUMENT HAS BEEN DETERMINED TO CONTAIN BASIC AND STABLE TECHNOLOGY WHICH IS NOT DYNAMIC IN NATURE.	
SAE AS81822/1	STABILIZED NOTICE THIS DOCUMENT HAS BEEN DECLARED "STABILIZED" BY THE AE-8 TECHNICAL COMMITTEE AND WILL NO LONGER BE SUBJECTED TO PERIODIC REVIEWS FOR CURRENCY. USERS ARE RESPONSIBLE FOR VERIFYING REFERENCES AND CONTINUED SUITABILITY OF TECHNICAL REQUIREMENTS. NEWER TECHNOLOGY MAY EXIST.	
		
CUSTODIAN: AE-8/AE-8D		
SAE values your input. To provide feedback on this Technical Report, please visit http://www.sae.org/technical/standards/AS81822/1A THIRD ANGLE PROJECTION 		
SAE Aerospace An SAE International Group AEROSPACE STANDARD WIRE, ELECTRICAL, SOLDERLESS WRAP, POLYETHYLENE TEREPHTHALATE-POLYESTER LAMINATED TAPE INSULATION, SILVER COATED SOLID CONDUCTOR SAE AS81822/1 SHEET 1 OF 4 REV. A		

SAENORM.COM : Click to view the full PDF of as81822_1a

ISSUED 1998-07 REAFFIRMED 2004-06 STABILIZED 2011-07

NOTICE

THIS DOCUMENT HAS BEEN TAKEN DIRECTLY FROM U.S. MILITARY SPECIFICATION MIL-W-81822/1A, NOTICE 1, AMENDMENT 1 AND CONTAINS ONLY MINOR EDITORIAL AND FORMAT CHANGES REQUIRED TO BRING IT INTO CONFORMANCE WITH THE PUBLISHING REQUIREMENTS OF SAE TECHNICAL STANDARDS. THE INITIAL RELEASE OF THIS DOCUMENT IS INTENDED TO REPLACE MIL-W-81822/1A, NOTICE 1, AMENDMENT 1. ANY PART NUMBERS ESTABLISHED BY THE ORIGINAL SPECIFICATION REMAIN UNCHANGED.

THE ORIGINAL MILITARY SPECIFICATION WAS ADOPTED AS AN SAE STANDARD UNDER THE PROVISIONS OF THE SAE TECHNICAL STANDARDS BOARD (TSB) RULES AND REGULATIONS (TSB 001) PERTAINING TO ACCELERATED ADOPTION OF GOVERNMENT SPECIFICATIONS AND STANDARDS. TSB RULES PROVIDE FOR (A) THE PUBLICATION OF PORTIONS OF UNREVISED GOVERNMENT SPECIFICATIONS AND STANDARDS WITHOUT CONSENSUS VOTING AT THE SAE COMMITTEE LEVEL, AND (B) THE USE OF THE EXISTING GOVERNMENT SPECIFICATION OR STANDARD FORMAT.

UNDER DEPARTMENT OF DEFENSE POLICIES AND PROCEDURES, ANY QUALIFICATION REQUIREMENTS AND ASSOCIATED QUALIFIED PRODUCTS LISTS ARE MANDATORY FOR DOD CONTRACTS. ANY REQUIREMENT RELATING TO QUALIFIED PRODUCTS LISTS (QPL'S) HAS NOT BEEN ADOPTED BY SAE AND IS NOT PART OF THIS TECHNICAL REPORT.

SAENORM.COM : Click to view the full PDF of as81822-1A

 An SAE International Group	AEROSPACE STANDARD	SAE AS81822/1 SHEET 2 OF 4	REV. A
	WIRE, ELECTRICAL, SOLDERLESS WRAP, POLYETHYLENE TEREPHTHALATE-POLYESTER LAMINATED TAPE INSULATION, SILVER COATED SOLID CONDUCTOR		

THE COMPLETE REQUIREMENTS FOR ACQUIRING THE WIRE DESCRIBED HEREIN SHALL CONSIST OF THIS SPECIFICATION AND THE ISSUE IN EFFECT OF SPECIFICATION MIL-W-81822.




TABLE I. Construction and performance details.

Part no. <u>1/</u>	Wire size (AWG)	Finished wire diameter (inches)	Finished weight (lb/1,000 ft) (max)	Cut-through load (grams)	Bend testing			Insulation pull-off (lbs)
					Mandrel diameter (ins.)		Tension load (lbs)	
					Heat resistance	Cold bend	Cold bend	
M81822/1-X30-*	30	0.0195 ± .0010	0.48	1400	1/16	1.0	0.25	0.4 to 2.5
M81822/1-X30V*	30	0.0180 ± .0010	0.45	1400	1/16	1.0	0.25	0.4 to 2.5
M81822/1-X28-*	28	0.0265 ± .0015	0.83	1800	5/64	1.0	0.50	0.5 to 2.5
M81822/1-X28V*	28	0.0255 ± .0015	0.80	1800	5/64	1.0	0.50	0.5 to 2.5
M81822/1-X26-*	26	0.0295 ± .0015	1.17	2200	3/32	1.0	0.50	1 to 4
M81822/1-X26V*	26	0.0265 ± .0015	1.08	2200	3/32	1.0	0.50	1 to 4
M81822/1-X24-*	24	0.0340 ± .0015	1.73	2600	7/64	1.0	0.50	1 to 4
M81822/1-X22-*	22	0.0390 ± .0020	2.58	2800	1/8	1.0	0.75	1 to 6
M81822/1-X20-*	20	0.0460 ± .0020	3.92	2900	9/64	1.0	0.75	1 to 6
M81822/1-X18-*	18	0.0540 ± .0030	6.00	3000	11/64	1.0	1.00	1 to 6

1/ PART NUMBER: The "X" in the generalized part numbers of table I shall be replaced by the designator for the conductor type and the asterisk shall be replaced by the code designator for the insulation color. Example: Size 24 wire with type A (soft annealed copper) conductor and white insulation - M81822/1-A24-9.

2/ Polyvinyl chloride laminant is not permitted.

WIRE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 105°C (221°F) MAX CONDUCTOR TEMPERATURE.

VOLTAGE RATING: 300 VOLTS (RMS).

INSULATION TENSILE STRENGTH: 2,500 PSI (MIN).

INSULATION ELONGATION: WIRE SIZES 30 AND 28 - 35 PERCENT (MIN).
WIRE SIZES 26 THROUGH 18 - 50 PERCENT (MIN).

COLOR: MIL-STD-104, CLASS 1, COLOR AS SPECIFIED IN CONTRACT OR ORDER. (ALL MIL-STD-104, CLASS 1, COLORS ARE AVAILABLE.)

SPARK TEST: 2,000 VOLTS (RMS).

INSULATION RESISTANCE: 500 MEGOHMS-1,000 FT (MIN).

WET DIELECTRIC TEST: 1,000 VOLTS (RMS), 60 Hz.

COLD BEND CONDITIONING: 4 HRS AT -54° ± 2°C (-65.2° ± 3.6°F).

DIELECTRIC TEST FOR CUT-THROUGH: 500 VOLTS (RMS), 60 Hz.

INSULATION HEAT RESISTANCE:
CONDITIONING, 48 HRS AT 150° ± 2°C (302° ± 3.6°F).
SHRINKAGE, 0.250 INCH (MAX).

 <i>An SAE International Group</i>	AEROSPACE STANDARD	SAE AS81822/1 SHEET 3 OF 4	REV. A
	WIRE, ELECTRICAL, SOLDERLESS WRAP, POLYETHYLENE TEREPHTHALATE-POLYESTER LAMINATED TAPE INSULATION, SILVER COATED SOLID CONDUCTOR		