
	SURFACE VEHICLE STANDARD		J997 MAR2013
		Issued	1967-08
		Reaffirmed	2013-03
		Superseding J997 JAN2000	
Spark Arrester Test Carbon			

RATIONALE

This document is currently valid for industry use.

1. Scope—This SAE Standard establishes physical properties required of SAE Coarse Test Carbon and SAE Fine Test Carbon and establishes test methods to ensure that these requirements are met.

1.1 Purpose—The purpose of this document is to establish specifications for test carbon to be used when performing the tests described in SAE J335, J342, and J350.

2. References

2.1 Applicable Publications—The following publications form a part of the specification to the extent specified herein. Unless otherwise indicated, the latest revision of SAE publications shall apply.

2.1.1 SAE PUBLICATIONS—Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

SAE J335—Multiposition Small Engine Exhaust System Fire Ignition Suppression

SAE J342—Spark Arrester Test Procedure for Large Size Engines

SAE J350—Spark Arrester Test Procedure for Medium Size Engines

2.1.2 ASTM PUBLICATIONS—Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM D 2854—Standard Test Method for Apparent Density of Activated Carbon

ASTM D 2862—Test Method for Particle Size Distribution of Granular Activated Carbon

ASTM D 3467—Test Method for Carbon Tetrachloride Activity of Activated Carbon

ASTM D 3802—Standard Test Method for Ball-Pan Hardness of Activated Carbon

ASTM E 11—Standard Specification for Wire Cloth Sieves for Testing Purposes

2.1.3 USDA FOREST SERVICE PUBLICATION—Available from USDA Forest Service, Technology and Development Center, 444 East Bonita Avenue, San Dimas, CA 91773-3198.

Spark Arrester Test Carbon Replacement Study, January 1991, USDA Forest Service

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2013 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
 Tel: +1 724-776-4970 (outside USA)
 Fax: 724-776-0790
 Email: CustomerService@sae.org
 SAE WEB ADDRESS: <http://www.sae.org>

**SAE values your input. To provide feedback
on this Technical Report, please visit
http://www.sae.org/technical/standards/J997_201303**

3. Test Carbon Requirements

3.1 Form—The test carbon shall be granular in form.

3.2 Size—The size distribution of particles of test carbon shall be as follows:

3.2.1 COARSE CARBON

- a. Pass through U.S. Standard No. 8 (2.36 mm) Sieve—100% by mass
- b. Retained on U.S. Standard No. 12 (1.70 mm) Sieve—60% by mass
- c. Retained on U.S. Standard No. 16 (1.18 mm) Sieve—40% by mass

3.2.2 FINE CARBON

- a. Pass through U.S. Standard No. 16 (1.18 mm) Sieve—100% by mass
- b. Retained on U.S. Standard No. 20 (850 μ m) Sieve—70% by mass
- c. Retained on U.S. Standard No. 30 (600 μ m) Sieve—30% by mass

3.2.3 MIXING—Before use, mix screened fractions by pouring from one container to another at least five times.

3.3 Activity—The test carbon shall conform to the commercial definition of “activated carbon.”

3.4 Apparent Density—0.450 to 0.520 g/mL when vibrated to a minimum volume (see 4.1).

3.5 Hardness—97.0% minimum (see 4.2).

3.6 Carbon Tetrachloride Activity—60% minimum (see 4.3).

4. Test Methods

4.1 Apparent Density—Determine the apparent density of the test sample, in accordance with ASTM Test Method D 2854.

4.2 Hardness—Determine the carbon particle hardness of the test sample, in accordance with ASTM Test Method D 3802.

4.3 Carbon Tetrachloride Activity—Determine the carbon tetrachloride activity of the test sample, in accordance with ASTM D 3467.

PREPARED BY THE SAE SPARK ARRESTER STANDARDS COMMITTEE

REAFFIRMED BY THE SAE SPARK ARRESTER STANDARDS COMMITTEE

APPENDIX A

A.1 Carbon Size—Experience has shown that commercial suppliers cannot consistently supply carbon that meets this document. For this reason, it is suggested that the user perform the final sieving of the carbon to obtain samples for test use. The following commercially available “rough-screened” carbon sieve analyses have proven to be satisfactory for final crushing and screening:

A.1.1 For Coarse Carbon—See Table A1.

TABLE A1—SUPPLIERS COARSE CARBON ROUGH SCREEN ANALYSIS SPECIFICATION

Retained on U.S. Standard Sieve No.	Mass %
8 (2.36 mm)	0–10
12 (1.70 mm)	40–60
16 (1.18 mm)	30–40
20 (850 μ m)	0–10
Pan	0–1

A.1.2 For Fine Carbon—See Table A2.

TABLE A2—SUPPLIERS FINE CARBON ROUGH SCREEN ANALYSIS SPECIFICATION

Retained on U.S. Standard Sieve No.	Mass %
14 (1.40 mm)	0–0.5
16 (1.18 mm)	10–30
20 (850 μ m)	50–70
30 (600 μ m)	0–25
Pan	0–5

A.2 Carbon Final Screening

A.2.1 Coarse Carbon—A quantity of rough-screened material may be sieved through a system of U.S. Standard Sieves 8 (2.36 mm), 12 (1.70 mm), and 16 (1.18 mm) (or their equivalent). Material retained on the No. 12 (1.70 mm) and No. 16 (1.18 mm) sieves is combined in the proportions specified under 3.2.1.

A.2.2 Fine Carbon—A quantity of rough-screened material may be sieved through a system of U.S. Standard Sieves 16 (1.18 mm), 20 (850 μ m), and 30 (600 μ m) (or their equivalent). Material retained on the No. 20 and No. 30 (600 μ m) sieve is combined in the proportions specified under 3.2.2.

A.2.3 Shaking—If a motorized vibrator shaker is used, material should be shaken in small quantities for approximately 10 min. If hand shaken, a longer shake period should be observed to assure that size segregation is complete.

A.3 Alternate Hardness Determination Method—One alternate method, which has been used to determine hardness, utilizes a cyclonic separator. This is acceptable if it provides equivalent hardness, +2%, to the method described in 4.2.